

**AWS A5.1/A5.1M:2025**  
**An American National Standard**

---

---

# **Specification for Carbon Steel Electrodes for Shielded Metal Arc Welding**



**AWS A5.1/A5.1M:2025  
An American National Standard**

**Approved by the  
American National Standards Institute  
September 30, 2024**

# **Specification for Carbon Steel Electrodes for Shielded Metal Arc Welding**

**15th Edition**

**Revises A5.1/A5.1M:2012**

Prepared by the  
American Welding Society (AWS) A5 Committee on Filler Metals and Allied Materials

Under the Direction of the  
AWS Technical Activities Committee

Approved by the  
AWS Board of Directors

## **Abstract**

This specification prescribes the requirements for classification of carbon steel covered electrodes used for shielded metal arc welding. The requirements include chemical composition and mechanical properties of weld metal, weld metal soundness, usability tests of electrodes, and moisture tests of the low-hydrogen electrode covering. Requirements for standard sizes and lengths, marking, manufacturing, and packaging are also included.

Optional supplemental requirements include tests for improved toughness and ductility, lower absorbed moisture in the electrode covering, and for diffusible hydrogen in the weld metal.

This specification makes use of both U.S. Customary Units and the International System of Units (SI). Since these are not equivalent, each system must be used independently of the other.



ISBN Print: 978-1-64322-344-5  
ISBN PDF: 978-1-64322-345-2  
© 2025 by American Welding Society  
All rights reserved  
Printed in the United States of America

**Photocopy Rights.** No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <[www.copyright.com](http://www.copyright.com)>.

## Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be revised, corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page ([www.aws.org](http://www.aws.org)). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex B). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS A5 Committee on Filler Metals and Allied Materials. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS A5 Committee on Filler Metals and Allied Materials and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS A5 Committee on Filler Metals and Allied Materials to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

# Personnel

## AWS A5 Committee on Filler Metals and Allied Materials

R. V. Decker, Chair	<i>Weldstar</i>
M. F. Sinfield, Vice Chair	<i>Naval Surface Warfare Center</i>
B. A. Pletcher, 2nd Vice Chair	<i>Bechtel Global Corporation</i>
K. R. Bulger, Secretary	<i>American Welding Society</i>
T. Anderson	<i>ITW—Miller Electric Manufacturing Company</i>
A. Boulianne	<i>CWB Group</i>
J. C. Bundy	<i>Hobart Brothers Company</i>
J. L. Caron	<i>Haynes International, Incorporated</i>
G. L. Chouinard	<i>Stoody Company (a division of ESAB)</i>
T. J. Eckardt	<i>Duke Energy</i>
D. A. Fink	<i>The Lincoln Electric Company</i>
R. J. Fox	<i>Hobart Brothers LLC</i>
M. James	<i>The Lincoln Electric Company</i>
S. D. Kiser	<i>Consultant</i>
S. J. Knostman	<i>Hobart Brothers Company</i>
L. G. Kvidahl	<i>Consultant</i>
F. B. Lake	<i>ESAB</i>
J. S. Lee	<i>Consultant</i>
C. McEvoy	<i>Naval Nuclear Laboratories—Knolls Atomic Power Laboratory</i>
T. Melfi	<i>The Lincoln Electric Company</i>
W. C. Mosier	<i>Polymet Corporation</i>
T. C. Myers	<i>Westec</i>
K. J. Roossinck	<i>Ingalls Shipbuilding</i>
K. Sampath	<i>Consultant</i>
J. D. Schaefer	<i>Y12 National Security Complex</i>
J. B. Schaeffer	<i>The Lincoln Electric Company</i>
W. S. Severance	<i>The Lincoln Electric Company</i>
D. Singh	<i>Consultant</i>
R. C. Sutherlin	<i>Richard Sutherlin PE Consulting LLC</i>
H. D. Wehr	<i>Arcos Industries</i>
J. Zhang	<i>Ohmstede, Limited</i>

**AWS A5A Subcommittee on Carbon and Low-Alloy Steel Electrodes  
and Rods for Shielded Metal Arc and Oxyfuel Gas Welding**

M. James, Chair	<i>The Lincoln Electric Company</i>
K. R. Bulger, Secretary	<i>American Welding Society</i>
R. V. Decker	<i>Weldstar</i>
S. J. Knostman	<i>Hobart Brothers Company</i>
J. A. Lipko	<i>Lipko Welding and Consulting, LLC</i>
D. Meyer	<i>ESAB Welding &amp; Cutting Products</i>
T. C. Myers	<i>Westec</i>
K. Sampath	<i>Consultant</i>
J. K. Zalokar	<i>The Lincoln Electric Company</i>

## Foreword

This foreword is not part of this standard but is included for informational purposes only.

This document makes use of both U.S. Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore, each system must be used independently of the other, without combining values in any way. In selecting rational metric units, AWS A1.1, *Metric Practice Guide for the Welding Industry* is used where suitable.

This specification is the latest revision of the first filler metal specification issued over 80 years ago. The initial 1940 document and the three revisions within the next five years were prepared by a joint committee of the American Society for Testing and Materials (ASTM) and the American Welding Society. However, they were issued with only an ASTM specification designation. The 1948 revision was the first specification issued with the AWS designation appearing on the document. The 1969 revision was the first time that the document was issued without the ASTM designation.

### Document Development:

ASTM A 233-40T	<i>Tentative Specifications for Iron and Steel Arc-Welding Electrodes</i>
ASTM A 233-42T	<i>Tentative Specifications for Iron and Steel Arc-Welding Electrodes</i>
ASTM A 233-43T	<i>Tentative Specifications for Iron and Steel Arc-Welding Electrodes</i>
ASTM A 233-45T	<i>Tentative Specifications for Iron and Steel Arc-Welding Electrodes</i>
ASTM A 233-48T	<i>Tentative Specifications for Mild Steel Arc Welding Electrodes</i>
AWS A5.1-48T	
ASTM A 233-55T	<i>Tentative Specifications for Mild Steel Arc Welding Electrodes</i>
AWS A5.1-55T	
ASTM A 233-58T	<i>Tentative Specification for Mild Steel Arc Welding Electrodes</i>
AWS A5.1-58T	
AWS A5.1-64T	<i>Tentative Specification for Mild Steel Covered Arc Welding Electrodes</i>
ASTM A 233-64T	
AWS A5.1-69	<i>Specification for Mild Steel Covered Arc Welding Electrodes</i>
ANSI W3.1-1973	
ANSI/AWS A5.1-78	<i>Specification for Carbon Steel Covered Arc-Welding Electrodes</i>
ANSI/AWS A5.1-81	<i>Specification for Carbon Steel Covered Arc-Welding Electrodes</i>
ANSI/AWS A5.1-91	<i>Specification for Carbon Steel Electrodes for Shielded Metal Arc Welding</i>
AWS A5.1/A5.1M:2004	<i>Specification for Carbon Steel Electrodes for Shielded Metal Arc Welding</i>
AWS A5.1/A5.1M:2012	<i>Specification for Carbon Steel Electrodes for Shielded Metal Arc Welding</i>

### Substantive changes in this document are shown in italic font and include:

- (1) *Computed Radiology (CR) and Digital Radiology (DR) have been added as options for radiographic inspection.*
- (2) *Fillet weld requirements have been adapted to facilitate measurement with fillet weld gauges.*
- (3) *E60-G and E70-G classifications have been added.*
- (4) *Grade 3 Radiographic Acceptance Standards were added for E7024 and E7024-1 classifications.*
- (5) *Table A.2 was deleted.*



The user's attention is called to the possibility that compliance with this standard may require use of an invention covered by patent rights. By publication of this standard, no position is taken with respect to the validity of any such claim(s) or of any patent rights in connection therewith. If a patent holder has filed a statement of willingness to grant a license under these rights on reasonable and nondiscriminatory terms and conditions to applicants desiring to obtain such a license, then details may be obtained from the standards developer.

Comments and suggestions for the improvement of this specification are welcome. They should be sent to the Secretary, Committee on Filler Metals and Allied Materials, American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

All errata to a standard shall be published in the *Welding Journal* and posted on the AWS website.

# Table of Contents

	<b>Page No.</b>
<i>Personnel</i> .....	v
<i>Foreword</i> .....	vii
<i>List of Tables</i> .....	x
<i>List of Figures</i> .....	x
<b>1. Scope</b> .....	1
<b>2. Normative References</b> .....	1
<b>3. Classification</b> .....	2
<b>4. Acceptance</b> .....	3
<b>5. Certification</b> .....	3
<b>6. Rounding Procedure</b> .....	3
<b>7. Summary of Tests</b> .....	3
<b>8. Retest</b> .....	3
<b>9. Weld Test Assemblies</b> .....	4
<b>10. Chemical Analysis</b> .....	5
<b>11. Radiographic Test</b> .....	5
<b>12. Tension Test</b> .....	6
<b>13. Bend Test</b> .....	6
<b>14. Impact Test</b> .....	6
<b>15. Fillet Weld Test</b> .....	7
<b>16. Moisture Test</b> .....	7
<b>17. Absorbed Moisture Test</b> .....	8
<b>18. Diffusible Hydrogen Test</b> .....	9
<b>19. Method of Manufacture</b> .....	9
<b>20. Standard Sizes and Lengths</b> .....	9
<b>21. Core Wire and Covering</b> .....	9
<b>22. Exposed Core</b> .....	9
<b>23. Electrode Identification</b> .....	9
<b>24. Packaging</b> .....	10
<b>25. Marking of Packages</b> .....	10
Annex A (Informative)—Guide to AWS Specification for Carbon Steel Electrodes for Shielded Metal Arc Welding .....	35
Annex B (Informative)—Requesting an Official Interpretation on an AWS Standard .....	51
AWS Filler Metal Specifications by Material and Welding Process .....	53
AWS Filler Metal Specifications and Related Documents .....	55

## List of Tables

<b>Table</b>	<b>Page No.</b>
1 Electrode Classification .....	11
2 Required Tests .....	12
3 Radiographic Soundness Requirements .....	15
4 Tension Test Requirements .....	15
5 Charpy V-Notch Impact Requirements .....	16
6 Chemical Composition Requirements for Weld Metal .....	17
7 Base Metal for Weld Test Assemblies.....	18
8 Requirements for Preparation of Fillet Weld Test Assemblies .....	19
9 Dimensional Requirements for Fillet Weld Usability Test Specimens .....	23
10 Moisture Content Limits for Electrode Coverings .....	23
11 Diffusible Hydrogen Requirements for Weld Metal .....	23
A.1 Typical Storage and Drying Conditions for Covered Arc Welding Electrodes .....	48
A.2 Discontinued Electrode Classifications.....	49

## List of Figures

<b>Figure</b>	<b>Page No.</b>
1 Order of Electrode Mandatory and Optional Supplemental Designators .....	24
2 Pad for Chemical Analysis of Undiluted Weld Metal.....	25
3 Groove Weld Test Assembly for Mechanical Properties and Soundness of Weld Metal Produced by Using All Electrode Classifications Except E6022 [E4322] and E7018M [E4918M] Electrodes .....	26
4 Fillet Weld Test Assembly for Usability of the Electrode .....	28
5 Groove Weld Test Assembly for Mechanical Properties and Soundness of Weld Metal Produced by Using E7018M [E4918M] .....	29
6 Test Assembly for Transverse Tension and Longitudinal Guided Bend Tests for Welds Made with E6022 [E4322] Electrodes .....	30
7 Welding Positions for Fillet Weld Test Assemblies .....	31
8A Radiographic Acceptance Standards for Rounded Indications (Grade 1) .....	32
8B Radiographic Acceptance Standards for Rounded Indications (Grade 2) .....	33
8C <i>Radiographic Acceptance Standards for Rounded Indications (Grade 3)</i> .....	34

# Specification for Carbon Steel Electrodes for Shielded Metal Arc Welding

## 1. Scope

**1.1** This specification prescribes requirements for the classification of carbon steel electrodes for shielded metal arc welding of carbon steels.

**1.2** This specification makes use of both U.S. Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore, each system must be used independently of the other without combining in any way when referring to material properties. The specification designated A5.1 uses U.S. Customary Units. The specification designated A5.1M uses SI Units. The latter units are shown within brackets [ ] or in appropriate columns in tables and figures. Standard dimensions based on either system may be used for sizing of filler metal or packaging or both under either the A5.1 or the A5.1M specification.

**1.3** Safety and health issues and concerns are beyond the scope of this standard; some safety and health information is provided, but such issues are not fully addressed herein. Some safety and health information can be found in Annex A, Clauses A5 and A10.

Safety and health information is available from the following sources:

American Welding Society:

- (1) ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*
- (2) AWS Safety and Health Fact Sheets
- (3) Other safety and health information on the AWS website

Material or Equipment Manufacturers:

- (1) Safety Data Sheets supplied by materials manufacturers
- (2) Operating Manuals supplied by equipment manufacturers

Applicable Regulatory Agencies.

Work performed in accordance with this standard may involve the use of materials that have been deemed hazardous and may involve operations or equipment that may cause injury or death. This standard does not purport to address all safety and health risks that may be encountered. The user of this standard should establish an appropriate safety program to address such risks as well as to meet applicable regulatory requirements. ANSI Z49.1 should be considered when developing the safety program.

## 2. Normative References

The documents listed below are referenced within this publication and are mandatory to the extent specified herein. For undated references, the latest edition of the referenced standard shall apply. For dated references, subsequent amendments to or revisions of any of these publications do not apply.

American Welding Society (AWS) documents:

*AWS A3.0M/A3.0*, Standard Welding Terms and Definitions, Including Terms for Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying