

AWS A5.5/A5.5M:2006
An American National Standard



Specification for Low-Alloy Steel Electrodes for Shielded Metal Arc Welding



American Welding Society



AWS A5.5/A5.5M: 2006
An American National Standard

Approved by the
American National Standards Institute
March 22, 2006

Specification for

Low-Alloy Steel Electrodes for

Shielded Metal Arc Welding

Supersedes ANSI/AWS A5.5-96

Prepared by the
American Welding Society (AWS) A5 Committee on Filler Metals and Allied Materials

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This specification prescribes the requirements for classification of low-alloy steel covered electrodes used for shielded metal arc welding. The requirements include chemical composition and mechanical properties of weld metal, weld metal soundness, usability tests of electrodes, and moisture tests of the low-hydrogen electrode covering. Requirements for standard sizes and lengths, marking, manufacturing, and packaging are also included.

Optional supplemental requirements include tests for absorbed moisture in the electrode covering and for diffusible hydrogen in the weld metal.

This specification makes use of both U.S. Customary Units and the International System of Units (SI). Since these are not equivalent, each system must be used independently of the other.



American Welding Society

550 N.W. LeJeune Road, Miami, FL 33126

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>Foreword</i>	vii
<i>List of Tables</i>	x
<i>List of Figures</i>	x
1. Scope	1
2. Normative References	1
3. Classification	2
4. Acceptance	12
5. Certification	12
6. Rounding-Off Procedure	12
7. Summary of Tests	12
8. Retest	12
9. Weld Test Assemblies	12
10. Chemical Analysis	15
11. Radiographic Test	17
12. Tension Test	20
13. Impact Test	24
14. Fillet Weld Test	26
15. Moisture Test	26
16. Absorbed Moisture Test	29
17. Diffusible Hydrogen Test	32
18. Method of Manufacture	32
19. Standard Sizes and Lengths	32
20. Core Wire and Covering	32
21. Exposed Core	33
22. Electrode Identification	33
23. Packaging	35
24. Marking of Packages	35
Annex A (Informative)—Guide to AWS Specification for Low-Alloy Steel Electrodes for Shielded Metal Arc Welding.....	37
Annex B (Informative)—Guidelines for the Preparation of Technical Inquiries.....	51
AWS Filler Metal Specifications by Material and Welding Process.....	53
AWS Filler Metal Specifications and Related Documents.....	55

List of Tables

Table	Page No.
1 Electrode Classification	3
2 Chemical Composition Requirements for Weld Metal	4
3 Tension Test Requirements	9
4 Charpy V-Notch Impact Requirements	11
5 Required Tests	13
6 Base Metal for Weld Test Assemblies	21
7 Preheat, Interpass, and Postweld Heat Treatment Temperatures	22
8 Requirements for Preparation of Fillet Weld Test Assemblies	25
9 Radiographic Soundness Requirements	29
10 Dimensional Requirements for Fillet Weld Usability Test Specimens	30
11 Moisture Content Limits in Low-Hydrogen Electrode Coverings	31
12 Diffusible Hydrogen Requirements for Weld Metal and Optional Supplemental Designators	32
13 Standard Sizes and Lengths	33
A.1 Comparison of Equivalent Classifications	40
A.2 Typical Storage and Drying Conditions for Covered Arc Welding Electrodes	43
A.3 Typical Amperage Ranges	44
A.4 Discontinued Electrode Classifications	49

List of Figures

Figure	Page No.
1 Pad for Chemical Analysis of Undiluted Weld Metal	15
2 Groove Weld Test Assembly for Mechanical Properties and Soundness of Weld Metal Produced by Using All Electrode Classifications Except E(X)XX18M(1)	16
3 Fillet Weld Test Assembly	18
4 Groove Weld Test Assembly for Mechanical Properties and Soundness of Weld Metal Produced by Using E(X)XX18M(1)	19
5 Welding Positions for Fillet Weld Test Assemblies	26
6A Radiographic Acceptance Standards for Rounded Indications (Grade 1)	27
6B Radiographic Acceptance Standards for Rounded Indications (Grade 2)	28
7 Dimensions of Fillet Welds	30
8 Alternate Methods for Facilitating Fracture of the Fillet Weld	31
9 Order of Electrode Mandatory and Optional Supplemental Designators	34

Specification for Low-Alloy Steel Electrodes for Shielded Metal Arc Welding

1. Scope

1.1 This specification prescribes requirements for the classification of low-alloy steel electrodes for shielded metal arc welding of carbon and low-alloy steels. These electrodes include steel alloys in which no single alloying element exceeds 10.5 percent.

1.2 Safety and health issues and concerns are beyond the scope of this standard and, therefore, are not fully addressed herein. Some safety and health information can be found in Informative Annex Clauses A5 and A10. Safety and health information is available from other sources, including, but not limited to, ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*, and applicable federal and state regulations.

1.3 This specification makes use of both U.S. Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore, each system must be used independently of the other without combining in any way when referring to material properties. The specification designated A5.5 uses U.S. Customary Units; and the specification designated A5.5M uses SI Units. The latter units are shown within brackets [] or in appropriate columns in tables and figures. Standard dimensions based on either system may be used for sizing of filler metal or packaging or both under A5.5 or A5.5M specification.

2. Normative References

2.1 The following standards contain provisions that, through reference in this text, constitute provisions of this AWS standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreement based on this AWS standard are encouraged to investigate the possibility of applying the most recent edition of the documents shown below. For undated references, the latest edition of the standard referred to applies.

2.2 The following AWS standards¹ are referenced in the normative sections of this document:

1. AWS A5.01, *Filler Metal Procurement Guidelines*
2. AWS A4.3, *Standard Methods for Determination of the Diffusible Hydrogen Content of Martensitic, Bainitic, and Ferritic Steel Weld Metal Produced by Arc Welding*
3. AWS A4.4M, *Standard Procedures for Determination of Moisture Content of Welding Fluxes and Welding Electrode Flux Coverings*
4. AWS B4.0 [B4.0M], *Standard Methods for Mechanical Testing of Welds*

2.3 The following ANSI standard² is referenced in the normative sections of this document:

1. ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*

2.4 The following ASTM standards³ are referenced in the normative sections of this document:

1. ASTM A 29/A 29M, *Standard Specification for Steel Bars, Carbon and Alloy, Hot-Wrought, General Requirements for*
2. ASTM A 36/A 36M, *Standard Specification for Carbon Structural Steel*
3. ASTM A 203/A 203M, *Standard Specification for Pressure Vessel Plates, Alloy Steel, Nickel*
4. ASTM A 204/A 204M, *Standard Specification for Pressure Vessel Plates, Alloy Steel, Molybdenum*
5. ASTM A 283/A 283M, *Standard Specification for Low and Intermediate Tensile Strength Carbon Steel Plates*

¹AWS standards are published by the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

²This ANSI standard is published by the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

³ASTM standards are published by the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.