

AWS A5.7/A5.7M:2026
An American National Standard

Specification for Copper and Copper-Alloy Bare Welding Rods and Electrodes



AWS A5.7/A5.7M:2026
An American National Standard

Approved by the
American National Standards Institute
November 18, 2025

Specification for

Copper and Copper-Alloy

Bare Welding Electrodes and Rods

8th Edition

Revises AWS A5.7/A5.7M:2007 (R2017)

Prepared by the
American Welding Society (AWS) A5 Committee on Filler Metals and Allied Materials

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This specification prescribes the requirements for classifications of copper and copper-alloy electrodes and rods for gas metal arc, gas tungsten arc, and plasma arc welding. Classification is based on chemical composition of the filler metal. Additional requirements are included for manufacture, sizes, lengths, and packaging. A guide is appended to the specification as a source of information concerning the classification system employed and intended use of the electrodes.

This specification makes use of both U.S. Customary Units and the International System of Units (SI). Since these are not equivalent, each system must be used independently of the other.



ISBN Print: 978-1-64322-412-1

ISBN PDF: 978-1-64322-413-8

© 2026 by American Welding Society

All rights reserved

Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <www.copyright.com>.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be revised, corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex B). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS A5 Committee on Filler Metals and Allied Materials. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS A5 Committee on Filler Metals and Allied Materials and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS A5 Committee on Filler Metals and Allied Materials to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Personnel

AWS A5 Committee on Filler Metals and Allied Materials

R. V. Decker, Chair	<i>Weldstar</i>
M. F. Sinfield, Vice Chair	<i>Naval Surface Warfare Center</i>
B. A. Pletcher, 2nd Vice Chair	<i>Bechtel Global Corporation</i>
K. R. Bulger, Secretary	<i>American Welding Society</i>
T. Anderson	<i>ITW—Miller Electric Manufacturing Company</i>
A. Boulianne	<i>Canadian Welding Bureau</i>
J. C. Bundy	<i>Hobart Brothers Company</i>
J. L. Caron	<i>Haynes International, Incorporated</i>
G. L. Chouinard	<i>WSI, an Avail Infrastructure Company</i>
T. J. Eckardt	<i>Duke Energy</i>
D. A. Fink	<i>Consultant</i>
R. J. Fox	<i>Hobart Brothers LLC</i>
M. James	<i>The Lincoln Electric Company</i>
S. J. Knostman	<i>Hobart Brothers Company</i>
L. G. Kvidahl	<i>Consultant</i>
F. B. Lake	<i>ESAB</i>
J. S. Lee	<i>Consultant</i>
C. McEvoy	<i>Naval Nuclear Laboratories—Knolls Atomic Power Laboratory</i>
T. Melfi	<i>The Lincoln Electric Company</i>
W. C. Mosier	<i>Polymet Corporation</i>
T. C. Myers	<i>Consultant</i>
K. J. Roossinck	<i>Ingalls Shipbuilding</i>
K. Sampath	<i>Consultant</i>
J. D. Schaefer	<i>Consolidated Nuclear Security</i>
J. B. Schaeffer	<i>The Lincoln Electric Company</i>
D. Singh	<i>Consultant</i>
R. C. Sutherlin	<i>Richard Sutherlin PE Consulting LLC</i>
H. D. Wehr	<i>Arcos Industries</i>
J. Zhang	<i>Consultant</i>

AWS A5F Subcommittee on Copper and Copper-Alloy Filler Metals

K. J. Roossinck, Chair	<i>Ingalls Shipbuilding</i>
K. R. Bulger, Secretary	<i>American Welding Society</i>
D. D. Dehner	<i>Harris Products Group</i>
P. Fischer	<i>Consultant</i>
J. D. Schaefer	<i>Consolidated Nuclear Security</i>
J. M. Turiff	<i>Wisconsin Wire Works Inc</i>
H. D. Wehr	<i>Arcos Industries</i>

This page is intentionally blank.

Foreword

This foreword is not part of this standard but is included for informational purposes only.

This document is the 7th revision of ANSI/AWS A5.7-84, first published in 1984. The AWS Subcommittee on Copper and Copper-Alloy Filler Metals prepared the revision. This specification describes the most common copper and copper-alloy bare rods and electrodes for use with the inert gas metal arc welding processes. Since the applications for these electrodes and rods are so diverse, i.e., surfacing and joining, discussions on intended uses and suggested welding parameters are included. The reader will find the data describing weld deposit hardness listed in Table A.2 particularly useful when selecting a classification for surfacing applications.

This document makes use of both U.S. Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore, each system must be used independently of the other, without combining in any way. In selecting rational metric units the AWS A1.1, *Metric Practice Guide for the Welding Industry*, and ISO 544: *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*, are used as guides. Tables and figures make use of both U.S. Customary and SI Units, which with the application of the specified tolerances provide for interchangeability of products in both U.S. Customary and SI Units.

Substantive changes included in this revision include revisions to subclause 1.3; 2. Normative References; 6. Rounding Procedure; 8. Retest; and Table 1 Chemical Composition Requirements. These substantive changes are shown in *italic* font.

Document Development

ASTM B 259-52T AWS A5.7-52T	<i>Tentative Specifications for Copper and Copper-Alloy Welding Rods</i>
ASTM B 259-57T AWS A5.7-57T	<i>Tentative Specifications for Copper and Copper-Alloy Welding Rods</i>
ASTM B 259-66T AWS A5.7-66T	<i>Tentative Specification for Copper and Copper-Alloy Welding Rods</i>
AWS A5.7-69 ANSI W3.7-73	<i>Specification for Copper and Copper Alloy Welding Rods</i>
AWS A5.7-77	<i>Specification for Copper and Copper Alloy Bare Welding Rods and Electrodes</i>
ANSI/AWS A5.7-84	<i>Specification for Copper and Copper Alloy Bare Welding Rods and Electrodes</i>
ANSI/AWS A5.7-84R	Reaffirmed June 19, 1991
ANSI/AWS A5.7-84R	Reaffirmed December 19, 2000
AWS A5.7/A5.7M:2007	<i>Specification for Copper and Copper-Alloy Bare Welding Rods and Electrodes</i>
AWS A5.7/A5.7M:2007 (R2017)	<i>Specification for Copper and Copper-Alloy Bare Welding Rods and Electrodes</i>

The user's attention is called to the possibility that compliance with this standard may require use of an invention covered by patent rights. By publication of this standard, no position is taken with respect to the validity of any such claim(s) or of any patent rights in connection therewith. If a patent holder has filed a statement of willingness to grant a license under these rights on reasonable and nondiscriminatory terms and conditions to applicants desiring to obtain such a license, then details may be obtained from the standards developer.

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, AWS A5 Committee on Filler Metals and Allied Materials, American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

All errata to a standard shall be published in the *Welding Journal* and posted on the AWS website.

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>Foreword</i>	vii
<i>List of Tables</i>	x
1. Scope	1
2. Normative References	1
3. Classification	2
4. Acceptance	2
5. Certification	2
6. Rounding Procedure	3
7. Summary of Tests	3
8. Retest	3
9. Chemical Analysis	3
10. Method of Manufacture	3
11. Standard Sizes and Shapes	3
12. Finish and Uniformity	4
13. Standard Package Forms	4
14. Winding Requirements	4
15. Filler Metal Identification	4
16. Packaging	5
17. Marking of Packages	5
Annex A (Informative)—Guide to AWS Specification for Copper and Copper-Alloy Bare Welding Rods and Electrodes	11
Annex B (Informative)—Requesting an Official Interpretation on an AWS Standard	19
AWS Filler Metal Specifications by Material and Welding Process	21
AWS Filler Metal Specifications and Related Documents	23

List of Tables

Table		Page No.
1	Chemical Composition Requirements	6
2	Standards Sizes	7
3	Standard Package Dimensions and Weights	8
A.1	Comparison of Specifications.....	16
A.2	Hardness and Tensile Strength of Copper and Copper-Alloy Weld Metal	16
A.3	Discontinued Classifications	17

List of Figures

Figure		Page No.
1	Dimensions of 4 in, 8 in, and 12 in [100 mm, 200 mm, and 300 mm] Spools.....	9

Specification for Copper and Copper-Alloy Bare Welding Rods and Electrodes

1. Scope

1.1 This specification prescribes requirements for the classification of copper and copper-alloy bare welding rods and electrodes for plasma arc, gas metal arc, and gas tungsten arc welding. It includes compositions in which the copper content exceeds that of any other element.¹

1.2 This specification makes use of both U.S. Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore, each system must be used independently of the other without combining in any way when referring to material properties. The specification with the designation A5.7 uses U.S. Customary Units. The specification A5.7M uses SI Units. The latter are shown within brackets [] or in appropriate columns in tables and figures. Standard dimensions based on either system may be used for sizing of filler metal or packaging or both under A5.7 or A5.7M specification.

1.3 Safety and health issues and concerns are beyond the scope of this standard; some safety and health information is provided, but such issues are not fully addressed herein. Some safety and health information can be found in Annex Clauses A5 and A10.

Safety and health information is available from the following sources:

American Welding Society:

- (1) ANSI Z49.1, Safety in Welding, Cutting, and Allied Processes*
- (2) AWS Safety and Health Fact Sheets*
- (3) Other safety and health information on the AWS website*

Material or Equipment Manufacturers:

- (1) Safety Data Sheets supplied by materials manufacturers*
- (2) Operating Manuals supplied by equipment manufacturers*

Applicable Regulatory Agencies

Work performed in accordance with this standard may involve the use of materials that have been deemed hazardous and may involve operations or equipment that may cause injury or death. This standard does not purport to address all safety and health risks that may be encountered. The user of this standard should establish an appropriate safety program to address such risks as well as to meet applicable regulatory requirements. ANSI Z49.1 should be considered when developing the safety program.

2. Normative References

The documents listed below are referenced within this publication and are mandatory to the extent specified herein. Unless otherwise defined in this document, welding terms are as defined in AWS A3.0M/A3.0. For undated references,

¹No attempt has been made to provide for classification of all grades of copper and copper-alloy filler metals; only the more commonly used have been included.