

AWS C2.25/C2.25M:2012 (R2026)
An American National Standard

Specification for Thermal Spray Feedstock—Wire and Rods



AWS C2.25/C2.25M:2012 (R2026)
An American National Standard

Approved by the
American National Standards Institute
September 5, 2012
Reaffirmed: March 26, 2026

Specification for Thermal Spray Feedstock—Wire and Rods

2nd Edition

Revises AWS C2.25/C2.25M:2012 (R2018)

Prepared by the
American Welding Society (AWS) C2 Committee on Thermal Spraying

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This specification provides the as-manufactured chemical composition classification requirements for solid and composite wires and ceramic rods for thermal spraying. Requirements for standard sizes, marking, manufacturing, and packaging are included.



ISBN Print: 978-1-64322-461-9

ISBN PDF: 978-1-64322-462-6

© 2026 by American Welding Society

All rights reserved

Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978)750-8400; Internet: www.copyright.com

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be revised, corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex A). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS C2 Committee on Thermal Spraying. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS C2 Committee on Thermal Spraying and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS C2 Committee on Thermal Spraying to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Personnel (Reaffirmation)

AWS C2 Committee on Thermal Spraying

D. C. Hayden, Chair	<i>Hayden Corporation</i>
J. Ryan, 1 st Vice Chair	<i>TECHMET ALLOYS, LLC</i>
D. A Lee, 2 nd Vice Chair	<i>David Lee Consulting LLC</i>
A. Celaya, Secretary	<i>American Welding Society</i>
W. J. Arata	<i>Steward Advanced Materials</i>
D. M. Beneteau	<i>CenterLine (Windsor) Limited</i>
C. C. Berndt	<i>Swinburne University of Technology</i>
M. M. Blasingame	<i>Superior Shot Peening, Inc.</i>
A. B. Duminie	<i>North American Höganäs Co.</i>
N. J. Latona	<i>Polymet Corporation</i>
C. Ma	<i>Curtiss-Wright Surface Technologies</i>
W. C. Mosier	<i>Polymet Corporation</i>
J. W. Rice	<i>Cimolai-HY</i>
K. Sampath	<i>Consultant</i>
C. A. Sauer	<i>Retired (NAVAIR)</i>
K. N. Tran	<i>Naval Surface Warfare Center</i>
M. Weinstein	<i>Wall Colmonoy Corporation</i>

Advisors to the AWS C2 Committee on Thermal Spraying

R. Ahmed	<i>Patronas Carigali Sdn Bhd.</i>
L. F. Grimenstein	<i>Stronghold Coating Systems</i>
J. O. Hayden	<i>Hayden Corporation</i>
I. R. Lasa	<i>Lasa and Associates Corrosion Services</i>
J. J. Medrano	<i>Oerlikon Metco.</i>
K. Sender	<i>Oerlikon Metco.</i>
C. Tudor	<i>International MetalFusion Corporation</i>

AWS C2J Subcommittee on Feedstock for Thermal Spray

N. J. Latona, Chair	<i>Polymet Corporation</i>
A. Celaya, Secretary	<i>American Welding Society</i>
M. M. Blasingame	<i>Superior Shot Peening, Inc.</i>
A. B. Duminie	<i>North American Höganäs Co.</i>
D. C. Hayden	<i>Hayden Corporation</i>
D. A. Lee	<i>David Lee Consulting LLC</i>
W. C. Mosier	<i>Polymet Corporation</i>
J. Ryan	<i>TECHMET ALLOYS, LLC</i>
J. D. Tetevuide	<i>Har-Bach Marketing, Inc.</i>
M. Weinstein	<i>Wall Colmonoy Corporation</i>

Advisors to the AWS C2J Subcommittee Feedstock for Thermal Spray

W. J. Arata	<i>Steward Advanced Materials</i>
J. O. Hayden	<i>Hayden Corporation</i>
K. L. Sender	<i>Oerlikon Metco.</i>

This page is intentionally blank.

Personnel (Original)

AWS C2 Committee on Thermal Spray

D.A. Lee, Chair	<i>Kennametal Stellite, Incorporated</i>
A.P. Yanski, Vice Chair	<i>Praxair TAFE</i>
E.H. Abrams, Secretary	<i>American Welding Society</i>
D. Beneteau	<i>Centerline (Windsor) Ltd</i>
M. Froning	<i>The Boeing Company</i>
L.F. Grimenstein	<i>Nation Coating Systems, Incorporated</i>
J.O. Hayden	<i>Hayden Corp</i>
R. McGrann	<i>Dept. of Mechanical Engineering</i>
W.M. Medford	<i>INSPEC, Incorporated</i>
B. Mosier	<i>Polymet Corp</i>
K. Sampath	<i>Consultant</i>
C. Sauer	<i>NAVAIR In-Service Support Center</i>
K.L. Sender	<i>Sulzer Metco</i>
M.F. Smith	<i>Sandia National Laboratories</i>
S. Szapra	<i>Naval Surface Warfare Center</i>
R.H. Unger	<i>Polymet Corp</i>
R.J. Wong	<i>Naval Surface Warfare Center</i>

Advisors to the AWS C2 Committee on Thermal Spray

D.A. Berardinelli	<i>Platt Brothers & Company</i>
C.C. Berndt	<i>Swinburne University of Technology</i>
R.S. Brunhouse	<i>A&A Co, Incorporated</i>
J.T. Butler	<i>Joseph T Butler, Incorporated</i>
B.T. Costello	<i>NAVSEA</i>
M.R. Dorfman	<i>Sulzer Metco (US), Incorporated</i>
A.J. Grubowski	<i>NAVSEA</i>
D. Guillen	<i>INEEL</i>
A. Roy	<i>Quality Calibration & Consulting</i>
E.F. Rybicki	<i>The University of Tulsa</i>
M. Weinstein	<i>Wall Colmonoy Corporation</i>
T.H. Via	<i>Via Technologies</i>

AWS C2J Subcommittee on Thermal Spray Feedstock

B. Mosier, Chair	<i>Polymet Corporation</i>
E.H. Abrams, Secretary	<i>American Welding Society</i>
W.J. Arata Jr.	<i>Carpenter Powder Products</i>
J. Dezelle	<i>Kennametal Energy Americas</i>
T. Glynn	<i>Sulzer Metco</i>
C.A. McAfee	<i>Hess Corporation</i>
A.P. Yanski	<i>Praxair TAFE</i>

Advisors to the AWS C2J Subcommittee on Thermal Spray Feedstock

J.O Hayden	<i>Hayden Corporation</i>
Frank Hermanek	<i>Praxiar Specialty Products</i>
Ed Rybicki	<i>The University of Tulsa</i>
R.H. Unger	<i>Polymet Corporation</i>
L.T. Vernam	<i>AlcoTec Wire Corporation</i>
M. Weinstein	<i>Wall Colmonoy Corporation</i>

Foreword

This foreword is not part of this standard but is included for informational purposes only.

This is a reaffirmation of the first revision of the specification, which was originally issued in 2002 and later revised in 2012. This document was developed by request of the U.S. Army Material Technology Center to supersede MIL-W-6712C, Metalizing Wire, with a U.S. National consensus standard. This revision describes a number of new feedstock materials.

The following editorial changes were included in the first reaffirmation:

The safety subclause was revised, notes a and b in Figure 2 and note a in Figure 3 were renumbered to 3 and 4, and 3, respectively; the references to notes a and b in Figure 2 and note a in Figure 3 were deleted from the figures; “ASTM” was changed to “ASTM International” in footnote 1; the title of ISO 544 was changed to “*Welding consumables—Technical delivery condition for filler materials and fluxes—Type of product, dimensions, tolerances and markings*”; the first “not” in 9 (2) was deleted; “the” was changed to “this” in 11.2.3, 12 (2), first sentence, third sentence, and last sentence.

The following editorial changes are included in this current reaffirmation:

The normative references clause was revised to reflect current boilerplate language. The clause now reads: “The documents listed below are referenced within this publication and are mandatory to the extent specified herein. For undated references, the latest edition of the referenced standard shall apply. For dated references, subsequent amendments or revisions of the publications may not apply since the relevant requirements may have changed.”

The headings for the referenced documents were revised to read “American Welding Society (AWS) standards,” “American Society of Testing and Materials (ASTM) standards,” and “International Organization for Standardization (ISO) standard.”

A reference to A3.0M/A3.0, *Standard Welding Terms and Definitions, Including Terms for Additive Manufacturing, Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying, and Nondestructive Examination* was added as a normative reference.

Footnotes 1, 2, and 3 were removed as it was part of the original boilerplate language.

The terms and definitions clause boilerplate was revised to remove “Including Terms for Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying.”

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, AWS C2 Committee on Thermal Spraying, American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>Foreword</i>	ix
<i>List of Tables</i>	xiii
<i>List of Figures</i>	xiii
1. General Requirements	1
1.1 Scope	1
1.2 Units of Measurement	1
1.3 Safety	1
2. Normative References	1
3. Terms and Definitions	2
4. Basis of Classification	2
5. Certification	2
6. Test Methods and Retest	8
6.1 Chemical Analysis	8
6.2 Retest	9
7. Method of Manufacture	9
8. Standard Sizes	9
9. Finish and Uniformity	9
10. Standard Packaging Forms	10
10.1 Coils with Support	11
10.2 Spools	11
10.3 Ceramics Rods	11
11. Winding Requirements	11
11.1 Winding	11
11.2 Cast and Helix	11
12. Solid and Composite Wire and Ceramic Rod Identification	12
13. Packaging	13
14. Marking of Packages	14
14.1 Product Information	14
14.2 Precautionary Information	14
Annex A (Informative)—Requesting an Official Interpretation on an AWS Standard	15
List of AWS Documents on Thermal Spraying	17

This page is intentionally blank.

List of Tables

Table		Page No.
1	Chemical Composition Requirements for Solid Ferrous Thermal Spray Wires	3
2	Chemical Composition Requirements for Solid Nonferrous Thermal Spray Wires	4
3	Chemical Composition for Cored Composite Thermal Spray Wires.	6
4	Chemical Composition Requirements for Thermal Spray Ceramic Rods	7
5	Standard Sizes for Bare Electrodes and Rods Using Solid Drawn or Composite (Tubular) Wire	10
6	Standard Sizes for Thermal Spray Ceramic Rods	10
7	Standard Packaging Dimensions and Weight for Thermal Spray Wires	11

List of Figures

Figure		Page No.
1	Thermal Spray Feedstock Classification System Format	8
2	Dimensions of Standard 12- and 14-in [300- and 355-mm] Spools	12
3	Dimensions of Standard 22-, 24-, and 30-in [560-, 610-, and 760-mm] Spools	13

This page is intentionally blank.

Specification for Thermal Spray Feedstock—Wire and Rods

1. General Requirements

1.1 Scope. This specification prescribes requirements for the classification of thermal spray feedstock based on the as manufactured chemical composition. Thermal Spray Feedstock includes solid and composite wires and ceramic rods for thermal spraying. Requirements for standard sizes, marking, manufacturing, and packaging are included.

1.2 Units of Measurement. This standard makes use of both U.S. Customary Units and the International System of Units (SI). The latter are shown within brackets ([]) or in appropriate columns in tables and figures. The measurements may not be exact equivalents; therefore, each system must be used independently.

1.3 Safety. Safety and health issues and concerns are beyond the scope of this standard and therefore are not addressed herein. Safety and health information is available from the following sources:

American Welding Society:

- (1) ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*
- (2) AWS Safety and Health Fact Sheets
- (3) Other safety and health information on the AWS website

Material or Equipment Manufacturers:

- (1) Safety Data Sheets supplied by materials manufacturers
- (2) Operating Manuals supplied by equipment manufacturers

Applicable Regulatory Agencies

Work performed in accordance with this standard may involve the use of materials that have been deemed hazardous, and may involve operations or equipment that may cause injury or death. This standard does not purport to address all safety and health risks that may be encountered. The user of this standard should establish an appropriate safety program to address such risks and meet applicable regulatory requirements. ANSI Z49.1 should be considered when developing the safety program.

2. Normative References

The documents listed below are referenced within this publication and are mandatory to the extent specified herein. For undated references, the latest edition of the referenced standard shall apply. For dated references, subsequent amendments or revisions of the publications may not apply since the relevant requirements may have changed.

American Welding Society (AWS) standards:

A3.0M/A3.0, *Standard Welding Terms and Definitions, Including Terms for Additive Manufacturing, Adhesive Bonding, Brazing, Soldering, Thermal Cutting, Thermal Spraying, and Nondestructive Examination*

ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*

American Society of Testing and Materials (ASTM) standards: