

**AWS C3.2M/C3.2:2019**  
**An American National Standard**



# **Standard Method for Evaluating the Strength of Brazed Joints**



**AWS C3.2M/C3.2:2019**  
**An American National Standard**

**Approved by**  
**American National Standards Institute**  
**November 30, 2018**

# **Standard Method for Evaluating the Strength of Brazed Joints**

**5th Edition**

**Supersedes AWS C3.2M/C3.2:2008**

Prepared by the  
American Welding Society (AWS) C3 Committee on Brazing and Soldering

Under the Direction of the  
AWS Technical Activities Committee

Approved by the  
AWS Board of Directors

## **Abstract**

This standard describes the test methods used to obtain brazed strength data of the short-time testing of single-lap joints in shear, butt-tension, stress-rupture, creep-strength, four-point-bending, and ceramic-tensile-button specimens. Specimen preparation methods, brazing procedures, testing techniques, and methods for data analysis are detailed. Sample forms for recording data are presented. A graphical method of data presentation relates shear stress to overlap distance.



ISBN PRINT: 978-1-64322-024-6  
ISBN PDF: 978-1-64322-025-3

© 2019 American Welding Society  
All rights reserved.

Printed in the United States of America

**Photocopy Rights.** No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: [www.copyright.com](http://www.copyright.com).

## Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be superseded by new editions. This standard may also be corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page ([www.aws.org](http://www.aws.org)). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex B). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS C3 Committee on Brazing and Soldering. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS C3 Committee on Brazing and Soldering and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS C3 Committee on Brazing and Soldering to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

## Foreword

This foreword is not part of this standard but is included for informational purposes only.

Over the years, design engineers have sought a standard methodology to measure the strength of brazed joints under various loading conditions. In 1963, the American Welding Society (AWS) Committee on Brazing and Soldering completed a project whose objective was to develop a brazed test specimen that, when tested, would result in reproducible data in a variety of laboratories at a minimum expenditure of time and money. The results of this project were described in AWS C3.1-63, *Establishment of a Standard Test for Brazing Joints*.

Nearly two decades later, this widely used document and test procedure was reviewed and updated as AWS C3.2-82, *Standard Method for Evaluating the Strength of Brazed Joints in Shear*.

A variety of test specimens have been developed both overseas and in the United States. Comparison of test data from a variety of sources has become increasingly difficult, if not impossible. Every test specimen design yields a different result; thus, it is imperative that the specimen geometry used for measuring the strength of brazed joints be standardized and that all strength data be obtained using standard specimens.

Test specimens have been included to provide additional design data for butt brazed joints, creep strength, stress rupture data, four-point bending specimens for testing of brazed ceramics and similar low-ductility materials, and a section addressing ceramic tensile button strength testing. That clause includes a discussion of the preparation of tensile button test specimens, brazing procedures, leak checking, and mechanical testing. This edition updates Figure 6.3 Butt Brazed Tensile Specimen geometry and includes a renumbering of tables and figures.

Underlined text or a vertical line in the margin indicates a revision of that item from the previous edition. Revisions to tables, figures, or annexes are marked with a vertical line in the margin.

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, AWS C3 Committee on Brazing and Soldering, American Welding Society, 8669 NW 36<sup>th</sup> Street, Suite 130, Miami, FL 33166.

# Table of Contents

	Page No.
<i>Personnel</i> .....	v
<i>Foreword</i> .....	ix
<i>List of Tables</i> .....	xiii
<i>List of Figures</i> .....	xiii
<b>1. General Requirements</b> .....	<b>1</b>
1.1 Scope .....	1
1.2 Units of Measurement .....	1
1.3 Safety .....	1
<b>2. Normative References</b> .....	<b>2</b>
<b>3. Terms and Definitions</b> .....	<b>2</b>
<b>4. Test Specimen and Procedures for the Testing of Single-Lap Joints in Shear</b> .....	<b>2</b>
4.1 Test Description .....	2
4.2 Specimen Preparation .....	2
4.3 Brazing Procedure .....	4
4.4 Postbrazing Procedure .....	7
4.5 Processing and Presentation of Data .....	7
<b>5. Test Specimen and Procedures for the Testing of Brazed Double-Lap Shear Specimen in Creep or Stress Rupture</b> .....	<b>9</b>
5.1 Test Description .....	9
5.2 Specimen Preparation .....	9
5.3 Brazing Procedure .....	10
5.4 Postbrazing Procedure .....	11
5.5 Recording of Data .....	11
5.6 Mechanical Testing .....	11
5.7 Processing and Presentation of Data .....	12
<b>6. Test Specimen and Procedures for Testing Butt Brazed Specimens in Tension</b> .....	<b>13</b>
6.1 Test Description .....	13
6.2 Specimen Preparation .....	13
6.3 Brazing Procedure .....	15
6.4 Postbrazing Procedure .....	15
6.5 Recording of Data .....	15
6.6 Mechanical Testing .....	15
<b>7. Test Specimen and Procedures for Testing the Four-Point Bend Specimen</b> .....	<b>16</b>
7.1 Test Description .....	16
7.2 Specimen Preparation .....	16
7.3 Brazing Procedure .....	17
7.4 Postbrazing Procedure .....	17
7.5 Recording of Data .....	17
7.6 Mechanical Testing .....	17
7.7 Processing and Presentation of Data .....	17

<b>8. Test Specimen Preparation and Procedures for Tensile Button Testing of <u>Ceramic-to-Ceramic or Ceramic-to-Metal Brazed Joints</u></b> .....	18
8.1 Test Description .....	18
8.2 Specimen Preparation .....	19
8.3 Procurement of Ceramic Tensile Buttons .....	19
8.4 Ceramic Tensile Button Parts .....	21
8.5 Brazing Procedure .....	21
8.6 Postbrazing Procedures .....	21
Annex A (Informative)—Informative References .....	27
Annex B (Informative)—Requesting an Official Interpretation on an AWS Standard .....	29
List of AWS Documents on Brazing and Soldering .....	31

## List of Tables

Table		Page No.
4.1	Suggested Overlap Distances for the Single-Lap Shear Specimen . . . . .	3
5.1	Suggested Overlap Distances for the Double-Lap Shear Specimen . . . . .	10
8.1	Dimensions for the Metallic Interlayer Used with Joint Types (C) and (D) . . . . .	20
8.2	List for Tensile Button Brazing Fixture Parts Shown in Figure 8.3. . . . .	24

## List of Figures

Figure		Page No.
4.1	Single-Lap Shear Test Specimen Blank . . . . .	3
4.2	Assembly of Single-Lap Shear Test Specimen and the Application of Brazing Filler Metal . . . . .	4
4.3	Tack Weld Fixture for Shear Test Specimen . . . . .	5
4.4	Typical Data Sheet for the Details of Single-Lap Specimen Preparation and Brazing . . . . .	6
4.5	Pin-Loaded Single-Lap Shear Test Specimen . . . . .	8
4.6	Average Stress as Function of Overlap Distance . . . . .	9
5.1	Assembly of Double-Lap Shear Test Specimens and the Application of Brazing Filler Metal . . . . .	11
5.2	Pin-Loaded Double-Lap Shear Test Specimen . . . . .	12
6.1	Method of Fabricating the Tensile Specimens Used to Obtain Data on the Mechanical Properties of Butt Brazed Joints. . . . .	14
6.2	Assembly of Blanks for Butt Brazed Tensile Specimen . . . . .	14
6.3	Butt Brazed Tensile Specimen . . . . .	16
7.1	Bend Specimens and Fixtures . . . . .	18
8.1	Still Image, Showing from Left to Right: (A) A Brazed Tensile Button Sample, Oriented Upright, (B) A Brazed Tensile Button Sample, on Its Side, (C) An Individual Tensile Button Piece That Has Been Metallized and Ni Plated, and (D) A Bare Ceramic Tensile Button Piece. . . . .	19
8.2	Fabrication Drawing for the Ceramic Tensile Button Specimen (Nominal Braze Cross Section = 113.3 mm <sup>2</sup> [0.17987 in <sup>2</sup> ]). . . . .	20
8.3	Brazing Fixture for ASTM F19 Tensile Specimen. . . . .	22
8.4	Schematic of Self-Aligning Grip for Tension Testing the Brazed Tensile Button Specimen . . . . .	24



# Standard Method for Evaluating the Strength of Brazed Joints

## 1. General Requirements

**1.1 Scope.** The purpose of this standard is to describe the test methods used to obtain reliable data on the strength of metallic-to-metallic, metallic-to-nonmetallic, and nonmetallic-to-nonmetallic brazed joints. Test specimens preparation and testing is described to provide consistent and proper fabrication, brazing practices, and test results. Interpretation of the test results is the responsibility of the user.

Documentation of the materials, brazing parameters, and test conditions are required to allow comparison of results with the joint strengths obtained by others using this standard method. General use of this standard method may permit a compilation of brazed joint strengths and brazing design criteria at some future time.

**1.2 Units of Measurement.** This standard makes use of both the International System of Units (SI) and U.S. Customary Units. The latter are shown in brackets ([ ]) or in appropriate columns in tables and figures. The measurements may not be exact equivalents; therefore each system must be used independently.

**1.3 Safety.** Safety and health issues and concerns are beyond the scope of this standard; some safety and health information is provided, but such issues are not fully addressed herein.

Safety and Health information is available from the following sources:

American Welding Society:

- (1) ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*
- (2) AWS Safety and Health Fact Sheets
- (3) Other safety and health information on the AWS website

Material or Equipment Manufacturers:

- (1) Safety Data Sheets supplied by the materials manufacturers
- (2) Operating Manuals supplied by equipment manufacturers

Applicable Regulatory Agencies

Work performed in accordance with this standard may involve the use of materials that have been deemed hazardous, and may involve operations or equipment that may cause injury or death. This standard does not purport to address all safety and health risks that may be encountered. The user of this standard should establish an appropriate safety program to address such risks as well as to meet applicable regulatory requirements. ANSI Z49.1 should be considered when developing the safety program.

## 2. Normative References

The documents listed below are referenced within this publication and are mandatory to the extent specified herein. For undated references, the latest edition of the referenced standard shall apply. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply.