

AWS C3.4M/C3.4:2026
An American National Standard

Specification for Torch Brazing



AWS C3.4M/C3.4:2026
An American National Standard

Approved by the
American National Standards Institute
December 8, 2025

Specification for

Torch Brazing

5th Edition

Revises AWS C3.4M/C3.4:2016

Prepared by the
American Welding Society (AWS) C3 Committee on Brazing and Soldering

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This specification presents the minimum fabrication, equipment, and process procedure requirements, as well as inspection requirements for the torch brazing of steels, stainless steels, copper, copper alloys, and heat- or corrosion-resistant alloys and other materials that can be adequately torch brazed (the torch brazing of aluminum alloys is addressed in AWS C3.7M/C3.7, *Specification for Aluminum Brazing*). This specification provides criteria for classifying torch brazed joints based on loading and the consequences of failure and quality assurance criteria defining the limits of acceptability in each class. The specification defines acceptable torch brazing equipment, materials, and procedures as well as the required inspection for each class of joint.



ISBN Print: 978-1-64322-416-9
ISBN PDF: 978-1-64322-417-6
© 2026 by American Welding Society
All rights reserved
Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: www.copyright.com.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be revised, corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex B). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS C3 Committee on Brazing and Soldering. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS C3 Committee on Brazing and Soldering and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS C3 Committee on Brazing and Soldering to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Personnel

AWS C3 Committee on Brazing and Soldering

R. A. Gourley, Chair	<i>Curtiss-Wright</i>
C. F. Darling, 1st Vice Chair	<i>The Prince & Izant Companies</i>
H. Zhao, 2nd Vice Chair	<i>Creative Thermal Solutions</i>
K. R. Bulger, Secretary	<i>American Welding Society</i>
G. L. Alexy	<i>Alexy Metals</i>
J. Arbogast	<i>The Gasflux Company</i>
J. A. Bush	<i>The Prince & Izant Companies</i>
D. Chalasani	<i>Morgan Advanced Materials</i>
E. Chen	<i>SpaceX</i>
K. E. Corona	<i>C/A Design</i>
W. M. Coughlan	<i>Metglas, Incorporated</i>
G. DeVries	<i>Radyne Corporation</i>
M. J. Disabb-Miller	<i>Northrup Grumman—Mission Systems</i>
P. J. Ditzel	<i>The Prince & Izant Companies</i>
T. C. Easley	<i>SEA Limited</i>
P. J. Fassman	<i>L3Harris Technologies</i>
S. L. Feldbauer	<i>Abbott Furnace Company</i>
M. T. Graham	<i>The Prince & Izant Companies</i>
T. D. Grohoske	<i>Wall Colmonoy Corporation</i>
T. Grøstad	<i>Höganäs AB</i>
J. H. Gutierrez	<i>Wall Colmonoy Corporation</i>
T. P. Hirthe	<i>Consultant</i>
D. A. Javernick	<i>Los Alamos National Laboratory</i>
J. A. Kapur	<i>Aimtek, Incorporated</i>
G. F. Kayser	<i>Aerojet Rocketdyne</i>
J. Krywicki	<i>Northrup Grumman—Mission Systems</i>
N. D. Kult	<i>Riverside Machine & Engineering</i>
K. P. Landgraf	<i>Lucas Milhaupt, Incorporated</i>
J. A. Liguori	<i>Ursa Major Technologies</i>
S. Lindsey	<i>Honeywell/Solstice Advanced Materials</i>
J. Longabucco	<i>Lucas-Milhaupt, Incorporated</i>
J. Machala	<i>Honeywell International, Inc.</i>
N. R. Marino	<i>RTX - Collins</i>
S. McAllister	<i>GH Induction Atmospheres LLC</i>
W. Miglietti	<i>Miglietti and Associates, LLC</i>
S. D. Nelson	<i>Rolls-Royce Corporation</i>
T. Oyama	<i>Morgan Advanced Ceramic—WESGO Metals Division</i>
M. E. Paponetti	<i>Solar Atmospheres</i>
J. Parnell	<i>Consultant</i>
A. M. Perfetti	<i>Thermal-Vac Technology, Inc.</i>
D. L. Pruchenski	<i>Consultant</i>
S. S. Rajan	<i>Raytheon</i>
M. E. Sapp	<i>NAVAIR-MRO Cherry Point</i>
B. T. Schneiderman	<i>Colorado School of Mines</i>

AWS C3 Committee on Brazing and Soldering (Continued)

A. E. Shapiro	<i>Titanium Brazing, Incorporated</i>
L. A. Shapiro	<i>Titanium Brazing, Incorporated</i>
R. W. Smith	<i>S-Bond Technologies</i>
M. Strojczek	<i>Höganäs AB</i>
E. Theisen	<i>EERC</i>
P. T. Vianco	<i>Consultant</i>
C. M. Volpe	<i>Senior Aerospace—Metal Bellows Division</i>
C. Walker	<i>Consultant</i>
M. Weinstein	<i>Wall Colmonoy Corporation</i>
M. J. Wilson	<i>Harris Products Group— A Lincoln Electric Company</i>
T. Wingers	<i>Wingers LLC</i>
Z. Yu	<i>Colorado School of Mines</i>

Advisors to the AWS C3 Committee on Brazing and Soldering

A. N. Jain	<i>Grainger Canada</i>
D. Kay	<i>Kay & Associates</i>
R. P. McKinney	<i>Consultant</i>
M. J. Pohlman	<i>Consultant</i>
E. T. Przybylowicz	<i>Honeywell Aerospace</i>
R. R. Xu	<i>Consultant</i>

AWS C3D Subcommittee on Brazing Specifications

S. S. Rajan, Chair	<i>Raytheon</i>
C. M. Volpe, 1st Vice Chair	<i>Senior Aerospace—Metal Bellows Division</i>
K. P. Landgraf, 2nd Vice Chair	<i>Lucas Milhaupt, Incorporated</i>
K. R. Bulger, Secretary	<i>American Welding Society</i>
J. A. Bush	<i>The Prince & Izant Companies</i>
E. Chen	<i>SpaceX</i>
K. E. Corona	<i>C/A Design</i>
W. M. Coughlan	<i>Metglas, Incorporated</i>
C. F. Darling	<i>The Prince & Izant Companies</i>
G. DeVries	<i>Radyne Corporation</i>
M. J. Disabb-Miller	<i>Northrup Grumman—Mission Systems</i>
P. J. Ditzel	<i>The Prince & Izant Companies</i>
P. J. Fassman	<i>L3Harris Technologies</i>
S. L. Feldbauer	<i>Abbott Furnace Company</i>
R. A. Gourley	<i>Curtiss-Wright</i>
M. T. Graham	<i>Prince & Izant Company</i>
T. D. Grohoske	<i>Wall Colmonoy Corporation</i>
T. Grøstad	<i>Höganäs AB</i>
J. H. Gutierrez	<i>Wall Colmonoy Corporation</i>
G. Hercik	<i>HI TecMetal Group</i>
T. P. Hirthe	<i>Consultant</i>
G. F. Kayser	<i>Aerojet Rocketdyne</i>
J. Krywicki	<i>Northrup Grumman—Mission Systems</i>
N. D. Kult	<i>Riverside Machine & Engineering</i>
J. A. Liguori	<i>Ursa Major Technologies</i>
S. Lindsey	<i>Honeywell/Solstice Advanced Materials</i>
J. Longabucco	<i>Lucas-Milhaupt, Incorporated</i>
J. Machala	<i>Honeywell International, Inc.</i>
N. R. Marino	<i>RTX—Collins</i>

AWS C3D Subcommittee on Brazing Specifications (Continued)

S. McAllister	<i>GH Induction Atmospheres LLC</i>
S. D. Nelson	<i>Rolls-Royce Corporation</i>
T. Oyama	<i>Morgan Advanced Ceramic—WESGO Metals Division</i>
M. E. Paponetti	<i>Solar Atmospheres</i>
J. Parnell	<i>Consultant</i>
A. M. Perfetti	<i>Thermal-Vac Technology, Inc.</i>
D. L. Pruchenski	<i>Consultant</i>
S. R. Santangelo	<i>Collins Aerospace</i>
B. T. Schneiderman	<i>Colorado School of Mines</i>
R. W. Smith	<i>S-Bond Technologies</i>
M. Strojczek	<i>Höganäs AB</i>
E. Theisen	<i>EERC</i>
P. T. Vianco	<i>Consultant</i>
C. Walker	<i>Consultant</i>
M. Weinstein	<i>Wall Colmonoy Corporation</i>
T. Wingens	<i>Wingens LLC</i>
Z. Yu	<i>Colorado School of Mines</i>
H. Zhao	<i>Creative Thermal Solutions</i>

Advisors to the AWS C3D Subcommittee on Brazing Specifications

G. L. Alexy	<i>Alexy Metals</i>
M. Eliades	<i>Consultant</i>
A. N. Jain	<i>Grainger Canada</i>
R. P. McKinney	<i>Consultant</i>
W. Miglietti	<i>Miglietti and Associates, LLC</i>
R. Oosthuysen	<i>Boyd Corporation</i>
M. J. Pohlman	<i>Consultant</i>
M. E. Sapp	<i>NAVAIR-MRO Cherry Point</i>
R. R. Xu	<i>Consultant</i>

This page is intentionally blank.

Foreword

This foreword is not part of this standard, but is included for informational purposes only.

This specification is one of a series prepared at the request of the Aerospace Materials Division (AMD) of the Society of Automotive Engineers (SAE) and a number of other organizations to replace the military specification MIL-B-7883, *Brazing of Steels, Copper, Copper Alloys, Nickel Alloys, Aluminum, and Aluminum Alloys*, which addressed all brazing processes. It became both obsolete and very cumbersome as brazing technology proliferated and became more complex.

Addressing all of the diverse brazing processes in one concise, easily understood document was found to be impractical; therefore, a series of five independent specifications on brazing have been written, all in the same format. These are the present document, AWS C3.4M/C3.4, *Specification for Torch Brazing*; AWS C3.5M/C3.5, *Specification for Induction Brazing*; AWS C3.6M/C3.6, *Specification for Furnace Brazing*; AWS C3.7M/C3.7, *Specification for Aluminum Brazing*; and AWS C3.9M/C3.9, *Specification for Resistance Brazing*.

The decision to subdivide the technology in this way was based on a survey of production brazing applications conducted by the AWS C3 Committee on Brazing and Soldering. The survey demonstrated that these five specifications would cover the vast majority of brazing performed today.

There is not a direct conversion of the MIL-B-7883 Grades and the AWS Classes and the quality assurance requirements differ. The cancellation of MIL-B-7883 was not intended to add additional inspection requirements to legacy hardware (i.e., MIL-B-7883 Grade B with only external inspection was not intended to become AWS Class B with internal NDT requirements). Each Organization Having Quality Responsibility must provide instructions on how or if the cancellation is to be handled for their hardware.

After the completion of the brazing specifications, it was determined that a document providing specific criteria and requirements for the application of ultrasonic testing to brazed joints was needed. Therefore, AWS C3.8M/C3.8, *Specification for the Ultrasonic Pulse-Echo Examination of Brazed Joints*, was written to complement this series.

This fifth edition supersedes AWS C3.4M/C3.4:2016, bearing the same title. Revisions made to this edition were coordinated with changes in AWS C3.5M/C3.5 and AWS C3.6M/C3.6. Revisions were made throughout the document. Underlined text or a vertical line in the margin indicates a revision from the previous edition.

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, AWS C3 Committee on Brazing and Soldering, American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>Foreword</i>	ix
1. General Requirements	1
1.1 Scope	1
1.2 Order of Authority	1
1.3 Units of Measurement	1
1.4 Safety	1
1.5 Ordering Information	2
2. Normative References	2
3. Terms and Definitions	3
4. Classification of Brazed Joints	4
4.1 Classification of Braze Joints	4
4.2 Class A—Critical Application	4
4.3 Class B—Semi-Critical Application	4
4.4 Class C—Noncritical Application	4
4.5 No Class Specified	4
5. Process Requirements	4
5.1 Process Description	4
5.2 Equipment	4
5.3 Materials	5
5.4 Brazing Procedure Specification Requirements	5
5.5 Brazing Procedure Specification (BPS) Qualification	7
5.6 Safety and Health—Supplemental	7
6. Quality Assurance Provisions	7
6.1 Responsibility for Inspection	7
6.2 Requirements for Compliance	8
6.3 Inspection Personnel Qualification	8
6.4 Sequence of Inspection and Manufacturing Operations	8
6.5 Required Inspection of Brazed Joints	8
6.6 Acceptance Criteria	10
Annex A (Informative)—Informative References	13
Annex B (Informative)—Requesting an Official Interpretation on an AWS Standard	15
List of AWS Documents on Brazing and Soldering	17

This page is intentionally blank.

Specification for Torch Brazing

1. General Requirements

1.1 Scope. This specification presents the minimum fabrication and quality requirements for the torch brazing of materials such as steels, stainless steels, copper, copper alloys, and heat- and corrosion-resistant alloys as well as other materials that can be adequately torch brazed. Note that the torch brazing of aluminum alloys is addressed in AWS C3.7M/C3.7, *Specification for Aluminum Brazing*.

The purpose of this specification is to standardize torch brazing process requirements and brazed joint quality requirements for all applications requiring brazed joints of assured quality. This document establishes minimum requirements for processes and products with minimum explanatory information so that sources of ambiguity are minimized. It assigns responsibility for the ultimate quality of the brazed product to a single organization and permits that organization to modify requirements if appropriate to the application. It requires proper documentation of any such modifications.

1.2 Order of Authority. The brazing process shall be subjected to the following order of authority, least-to-highest: this specification, assembly drawing, contract or purchase order, and the Organization Having Quality Responsibility (OHQR). That is, the final responsibility for all aspects of the brazing process (including, but not limited to, materials, equipment, heating cycle, calibration, etc.) and brazed assembly quality (including, but not limited to, inspection methods, inspection criteria, rework, etc.) rests with the OHQR. The OHQR has the authority to make any modifications to the requirements document(s) and to stipulate those modifications to the brazing operator. Any such modifications shall be fully documented by the OHQR.

1.3 Units of Measurement. This standard makes use of both the International System of Units (SI) and U.S. Customary Units; the latter are shown within brackets [] or in appropriate columns in tables and figures. The measurements may not be exact equivalents; therefore, each system must be used independently.

1.4 Safety. Safety and health issues and concerns are beyond the scope of this standard; some safety and health information is provided, but such issues are not fully addressed herein.

Safety and Health information is available from the following sources:

American Welding Society:

- (1) ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*
- (2) AWS Safety and Health Fact Sheets
- (3) Other safety and health information on the AWS website

Material or Equipment Manufacturers:

- (1) Safety Data Sheets supplied by the materials manufacturers
- (2) Operating Manuals supplied by equipment manufacturers

Applicable Regulatory Agencies:

- (1) United States Department of Labor, Occupational Safety & Health Administration (OSHA)
- (2) Equivalent agencies of other countries and individual states

Work performed in accordance with this standard may involve the use of materials that have been deemed hazardous, and may involve operations or equipment that may cause injury or death. This standard does not purport to address all safety and health risks that may be encountered. The user of this standard should establish an appropriate safety program