


AWS C4.4/C4.4M:2007
An American National Standard



Recommended Practices for Heat Shaping and Straightening with Oxyfuel Gas Heating Torches



American Welding Society



**AWS C4.4/C4.4M:2007
An American National Standard**

**Approved by the
American National Standards Institute
September 11, 2007**

Recommended Practices for Heat Shaping and Straightening with Oxyfuel Gas Heating Torches

2nd Edition

Supersedes AWS C4.4/C4.4M:2004

Prepared by the
American Welding Society (AWS) C4 Committee on Oxyfuel Gas Welding and Cutting

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This second edition of Recommended Practices for Heat Shaping and Straightening covers the shaping of metal products by prudent use of heat to obtain a desired configuration. The text reviews the theory and analytical calculations that explain how heat shaping and straightening occurs. Sample calculations and tables are presented for typical materials. General heating patterns and heat shaping and straightening techniques are discussed. Specific heating applications are illustrated for various sections.



American Welding Society

550 N.W. LeJeune Road, Miami, FL 33126

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>Foreword</i>	vii
<i>List of Tables</i>	xi
<i>List of Figures</i>	xi
1. Scope	1
2. Normative References	1
3. Terms and Definitions	2
4. Theory of Heat Shaping	2
5. Distortion	6
6. Fundamentals and Precautions	7
7. Equipment and Supplies	8
7.1 Standard Equipment.....	8
7.2 Special Equipment.....	8
7.3 Oxygen Supply.....	8
7.4 Fuel Supply.....	8
7.5 Maximum Acetylene Pressure.....	9
7.6 Pressure Regulators.....	9
7.7 Hoses and Fittings.....	11
7.8 Heating Torches.....	12
7.9 Heating Tip/Head.....	12
7.10 Maintenance of Heating Tips or Heads.....	12
7.11 Personal Protective Equipment (PPE).....	13
7.12 Safe Use, Handling, and Storage of Gas Cylinders.....	14
8. Startup and Shutdown Procedure	15
8.1 Setting Up Equipment.....	15
8.2 Lighting the Torch.....	16
8.3 Equipment Shutdown.....	17
8.4 Equipment Not in Use.....	17
8.5 Reuse of Equipment Already Connected.....	17
9. Flame Adjustment	17
9.1 Types of Flames.....	17
9.2 Flashback Arrestors and Check Valves.....	18
10. General Technique	19
11. Procedures for General Applications	20
11.1 Mechanically Restrained Structures.....	20
11.2 Freestanding Unrestrained Members.....	21
11.3 Shaping of Plate.....	23
11.4 Flattening Plates.....	23
11.5 Plate Tightening.....	23

	Page No.
12. Procedures for Specific Applications	23
12.1 Bending of Flat Bar, V Heat.....	23
12.2 Bending of Channel, V Heat.....	26
12.3 Bending of Beams.....	26
12.4 Bending of Angle.....	27
12.5 Bending of T Sections	27
12.6 Bending of Plate	30
12.7 Pipe	30
13. Line Heating and Flame Bending in Shipyards	30
13.1 Background.....	30
13.2 Basic Concepts.....	32
13.3 Planning and Methods	32
13.4 Recommended Practices.....	33
13.5 Code Compliance.....	33
13.6 Conclusions	33
14. Safety and Health	33
Annex A (Informative)—Informative References	35
Annex B (Informative)—Fuel Gas Withdrawal Rates	39
Annex C (Informative)—Guidelines for the Preparation of Technical Inquiries.....	41
List of AWS Documents on Oxyfuel Gas Welding and Cutting.....	43

List of Tables

Table	Page No.
B.1 Acetylene Withdrawal.....	39
B.2 Methylacetylene-Propadiene Stabilized (MPS) Withdrawal	39
B.3 Propylene Withdrawal.....	40
B.4 Propane Withdrawal.....	40

List of Figures

Figure	Page No.
1 Shortening of Bar from Application of Heat	3
2 Variation in Yield Strength and Modulus of Elasticity with Respect to Temperature for ASTM A 36 Steel.....	4
3 Imperceptible Welding Distortion of a Thick Steel Plate	5
4 Welding Distortion of a Thin Steel Plate	7
5 Oxygen Cylinder	9
6 Typical Fuel Gas Cylinders.....	9
7 Pressure Regulators.....	10
8 Hoses and Fittings.....	11
9 Manual Heating Torch	12
10 Multi-Flame Heating Heads.....	13
11 Water-Cooled Flame Hardening Head.....	13
12 Carburizing Flame.....	18
13 Neutral Flame.....	18
14 Oxidizing Flame.....	18
15 Basic Heating Patterns	20
16 Externally Restrained Plate	21
17 Externally Restrained Beam.....	21
18 V Shape Heat Pattern for Straightening or Shaping a Flat Bar.....	22
19 Dimensions for Calculating Upset	23
20 Behavior of ASTM A 36 Steel Perfectly Confined in One Axis as a Function of Temperature.....	24
21 Heat Patterns in Rolled Shapes	25
22 Spot Heat Repair of Dent in Plate	25
23 Spot Heat Repair (Tightening) on Irregular Plate.....	26
24 Application of V Shape Heat Pattern and Direction of Movement	26
25 Bending of Channel Toward Flange	27
26 Bending of Channel Toward Web	27
27 Bending of Channel Toward Open Side	27
28 Bending of Beam Toward Open Side	28
29 Bending of Beam Toward Flange	28
30 Bending of Angle Toward Face of Leg	28
31 Bending of Angle Toward Edge of Leg.....	29
32 Bending of T Section Toward Web	29

Figure		Page No.
33	Bending of T Section Toward Flange	29
34	Bending of Plate	29
35	Bending of Plate (More Movement)	30
36	Decreasing Diameter of Heavy Wall Pipe	31
37	Straightening of Pipe or Round	31
38	Straightening Pipe or Round Stock—V Shape Heating with Serpentine Path	31
39	Straightening Pipe or Round Stock—V Shape Heating with Line Heating Pattern	32

Recommended Practices for Heat Shaping and Straightening with Oxyfuel Gas Heating Torches

1. Scope

This publication describes some causes of distortion and corrective actions through the use of heat. It also describes some heat shaping techniques and the direction of movement expected in the heated metal. Equations are provided to aid in estimating the amount of movement for a given heating technique. The methods discussed are specifically applicable to ferrous metals, but many of the methods can be applied to nonferrous metals as well. For a more comprehensive description of specific applications, see Annex A, Informative References.

Heat has been used to shape and straighten structural elements in bridges, buildings, and marine constructions for over a hundred years. Since the late 1930s, the use of oxyfuel gas torches to do this work has become more prevalent. This publication is a recommended practice for using the torch process for work on bridges and buildings, and to some extent, shipbuilding.

Mechanical forces in fabrication and erection, forces occurring in service, accidental impacts from external forces, fire, and explosion, all cause stress in a structural member or a part of a member. If that stress exceeds the elastic limit of the material, distortion will occur, and the member will not conform to its desired shape. Heat shaping and straightening is an economical method to produce the desired movement to bring the member into conformance.

The shipbuilding industry throughout the world has taken heat shaping to new heights in shaping technology. Particularly, the use of line heating to shape complex curves in hull structures has become an integral part of a group technology in shipbuilding which also includes product work packages and accuracy control.

Basically, straightening and shaping involves controlled thermal expansion and contraction of a structural element. The method, location, and shape of the heat application are covered briefly in this publication. This

recommended practice is limited to fundamentals and simple applications (see Annex A for additional information).

This standard makes use of both U.S. Customary Units and the International System of Units (SI). The latter are shown within brackets [] or in appropriate columns in tables and figures. The measurements may not be exact equivalents; therefore, each system must be used independently.

Safety and health issues may not be fully addressed by this standard. Users of this standard should consult ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*, applicable federal, state, and local regulations and other relevant documents concerning safety and health issues not addressed herein.

2. Normative References

The following standard contains provisions, which, through reference in this text, constitute mandatory provisions of this AWS standard. For undated references, the latest edition of the referenced standard shall apply. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply.

AWS documents:¹

AWS A3.0, *Standard Welding Terms and Definitions, Including Terms for Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying*; and

AWS F4.1, *Recommended Safe Practices for Preparation for Welding and Cutting of Containers and Piping*.

Other documents:

ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*;²

¹ AWS standards are published by the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

² ANSI Z49.1 is published by the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.