



Structural Welding Code— Reinforcing Steel

**Including Metal
Inserts and
Connections in
Reinforced Concrete
Construction**



American Welding Society



**AWS D1.4/D1.4M:2011
An American National Standard**

**Approved by the
American National Standards Institute
January 31, 2011**

Structural Welding Code— Reinforcing Steel

Including
Metal Inserts and Connections
in Reinforced Concrete
Construction

7th Edition

Supersedes AWS D1.4/D1.4M:2005

Prepared by the
American Welding Society (AWS) D1 Structural Welding Committee

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This code covers the requirements for welding reinforcing steel in most reinforced concrete applications. It contains a body of rules for the regulations of welding reinforcing steel and provides suitable acceptance criteria for such welds.



American Welding Society

550 N.W. LeJeune Road, Miami, FL 33126

International Standard Book Number: 978-0-87171-786-3
American Welding Society
550 N.W. LeJeune Road, Miami, FL 33126
© 2011 by American Welding Society
All rights reserved
Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <www.copyright.com>.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions are entrusted to appropriately qualified and competent personnel.

This standard may be superseded by the issuance of new editions. Users should ensure that they have the latest edition.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

Finally, the AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

On occasion, text, tables, or figures are printed incorrectly, constituting errata. Such errata, when discovered, are posted on the AWS web page (www.aws.org).

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Technical Services Division, 550 N.W. LeJeune Road, Miami, FL 33126 (see Annex C). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS D1 Committee on Structural Welding. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS D1 Committee on Structural Welding and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS D1 Committee on Structural Welding to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

This page is intentionally blank.

Personnel

AWS D1 Committee on Structural Welding

| | |
|-------------------------------|---|
| D. K. Miller, Chair | <i>The Lincoln Electric Company</i> |
| A. W. Sindel, 1st Vice Chair | <i>Alstom Power, Incorporated</i> |
| T. L. Niemann, 2nd Vice Chair | <i>Minnesota Department of Transportation</i> |
| S. Morales, Secretary | <i>American Welding Society</i> |
| N. J. Altebrando | <i>STV, Incorporated</i> |
| F. G. Armao | <i>The Lincoln Electric Company</i> |
| E. L. Bickford | <i>Acute Technological Services</i> |
| B. M. Butler | <i>Walt Disney World Company</i> |
| R.D. Campbell | <i>Bechtel National, Incorporated</i> |
| H. H. Campbell III | <i>Pazuzu Engineering</i> |
| L. E. Collins | <i>Team Industries, Incorporated</i> |
| R. B. Corbit | <i>Exelon Nuclear Corporation</i> |
| R. A. Dennis | <i>Consultant</i> |
| M. A. Grieco | <i>Massachusetts Department of Transportation</i> |
| C. W. Holmes | <i>Modjeski and Masters, Incorporated</i> |
| J. J. Kenney | <i>Shell International E & P</i> |
| J. H. Kiefer | <i>ConocoPhillips Company</i> |
| V. Kuruvilla | <i>Genesis Quality Systems</i> |
| J. Lawmon | <i>American Engineering & Manufacturing, Incorporated</i> |
| N. S. Lindell | <i>Inspectech Incorporated</i> |
| D. R. Luciani | <i>Canadian Welding Bureau</i> |
| S. L. Luckowski | <i>Department of the Army</i> |
| P. W. Marshall | <i>MHP Systems Engineering</i> |
| M. J. Mayes | <i>Mayes Testing Engineers, Incorporated</i> |
| D. L. McQuaid | <i>D. L. McQuaid and Associates, Incorporated</i> |
| R. D. Medlock | <i>High Steel Structures, Incorporated</i> |
| J. Merrill | <i>MACTEC, Incorporated</i> |
| J. B. Pearson, Jr. | <i>LTK Engineering Services</i> |
| D. C. Phillips | <i>Hobart Brothers Company</i> |
| D. D. Rager | <i>Rager Consulting, Incorporated</i> |
| R. E. Shaw, Jr. | <i>Steel Structures Technology Center, Incorporated</i> |
| T. J. Schlafly | <i>American Institute of Steel Construction</i> |
| D. R. Scott | <i>PSI (Retired)</i> |
| R. W. Stieve | <i>Greenman-Pederson, Incorporated</i> |
| M. M. Tayarani | <i>Massachusetts Department of Transportation</i> |
| K. K. Verma | <i>Federal Highway Administration</i> |
| B. D. Wright | <i>Advantage Aviation Technologies</i> |

Advisors to the D1 Committee on Structural Welding

| | |
|-------------------|--|
| W. G. Alexander | <i>WGAPE</i> |
| E. M. Beck | <i>MACTEC, Incorporated</i> |
| O. W. Blodgett | <i>The Lincoln Electric Company (Retired)</i> |
| G. L. Fox | <i>Consultant</i> |
| G. J. Hill | <i>G. J. Hill and Associates, Incorporated</i> |
| M. L. Hoitomt | <i>Hoitomt Consulting Services</i> |
| D. R. Lawrence II | <i>Blue Scoep Steel (Retired)</i> |
| *W. A. Milek, Jr. | <i>Consultant</i> |

* Deceased

| | |
|----------------|---|
| J. E. Myers | <i>Consultant</i> |
| J. W. Post | <i>J. W. Post and Associates, Incorporated</i> |
| P. J. Sullivan | <i>Massachusetts Department of Transportation (Retired)</i> |

AWS D1I Subcommittee on Reinforcing Steel

| | |
|--------------------------|--|
| J. Merrill, Chair | <i>Mactec Engineering and Consulting</i> |
| N.S. Lindell, Vice Chair | <i>Inspectech Incorporated</i> |
| M. E. Gase | <i>Soils and Materials Engineers, Incorporated</i> |
| D. P. Gustafson | <i>Consultant</i> |
| T. Huerter | <i>Professional Service Industries</i> |
| E. D. Pratt | <i>Hanson Structural Precast</i> |
| D. R. Scott | <i>PSI (Retired)</i> |
| T.W. Stuebaker | <i>Terracon Consultants</i> |

Advisors to AWS D1I Subcommittee on Reinforcing Steel

| | |
|-------------|--|
| K. Landwehr | <i>Schuff Steel Company</i> |
| M. J. Mayes | <i>Mayes Testing Engineers, Incorporated</i> |
| J. E. Myers | <i>Consultant</i> |
| D. D. Rager | <i>Rager Consulting, Incorporated</i> |

Foreword

This foreword is not part of AWS D1.4/D1.4M:2011, *Structural Welding Code—Reinforcing Steel*, but is included for informational purposes only.

In 1961, the American Welding Society published its first reinforcing steel welding standard, AWS D12.1-61, *Recommended Practices for Welding Reinforcing Steel, Metal Inserts and Connections in Reinforced Concrete Construction*. The D12 Committee was disbanded some time after publication of the 1961 code and before publication of the 1975 edition.

The 1961 document was replaced with a greatly revised version, AWS D12.1-75, *Reinforcing Steel Welding Code*, with the format patterned after the AWS D1.1-72, *Structural Welding Code*. The 1975 code was produced by the AWS Structural Welding Committee but was not renumbered to reflect this committee change. As with ANSI/AWS D1.1, AWS D12.1-75 was designed as a self-contained code, including within it the qualification of welders and procedures, and requirements for workmanship, quality, and inspection.

The listings of materials and welding processes were revised in the D12.1-75 code. Items newly introduced were the carbon equivalent method for determining preheat, the parenthetical inclusion of metric (SI) conversions, and the two different methods of joint strength determination.

The AWS D12.1-75 document was revised and the title changed to ANSI/AWS D1.4-79, *Structural Welding Code—Reinforcing Steel*. Since the 1979 edition of ANSI/AWS D1.4, *Structural Welding Code—Reinforcing Steel*, was issued, further use by designers, engineers, and fabricators has necessitated a number of changes to the requirements; the 1992, 1998, and 2005 editions reflected these changes. This edition, AWS D1.4/D1.4M:2011, has additional revisions.

The following is a summary of the significant technical revisions in this edition:

1. Subclause 1.2.1 was revised to address precast concrete components.
2. New definitions were added under 1.5.
3. Safety information was clarified in 1.7.
4. Figure 2.1 was revised to clarify the centerline, nominal radius, and effective throat.
5. Subclause 3.2.1 was revised to address indirect butt joints.
6. Figure 3.2 was updated to illustrate degree ranges in all sketches.
7. Figures 3.3 and 3.4 were revised to restrict the gaps between bars to nothing over 1/4D or 3/16 in [5 mm], whichever is less.
8. Subclause 4.4.2 was modified to differentiate between the sum of maximum dimensions of all porosity versus maximum dimensions of any single porosity or fusion-type discontinuity.
9. New subclause 5.1.3 was added to address coated reinforcing steel and filler metal selection.
10. Subclause 5.3 was added to list requirements for maximum wind velocity and minimum ambient temperature.
11. New subclauses 5.10 and 5.11 were added to restrict electrodes used for GMAW and FCAW.
12. Subclause 5.12 was added to restrict the shielding gas used for GMAW and FCAW-G.
13. Table 5.1 was updated to meet the most current A5 specifications.
14. Clause 6 was revised to list the details for fillet weld prequalified essential variables.
15. New Table 6.1 lists the prequalified essential variables for fillet welds.
16. The essential variable requiring requalification for a change in the shape or any one type of groove was removed from Table 6.2.
17. Table 6.4 was corrected to include lap joints in indirect butt joints.
18. New Table 6.5 was added to clarify acceptance criteria for macroetch.
19. Figure 6.4 was updated.
20. All sketches in Figures 6.5 and 6.6 were redrawn for clarity.
21. New Figure 6.7 was added to illustrate welder qualification tests for fillet weld to plate.

22. Figures 7.1 and 7.2 were redrawn to increase the backing to 3/16 in [5 mm].

23. Annex B was updated.

Changes in Code Requirements. Underlined text in the subclauses, tables, or figures indicates an editorial or technical change from the 2005 edition. A vertical line in the margin indicates a revision from the 2005 edition.

Informative Annexes. These annexes are not code requirements but are provided to clarify code provisions by showing examples, providing information, or suggesting alternative good practices.

Errata. It is the Structural Welding Committee's Policy that all errata should be made available to users of the code. Therefore, any significant errata will be published in the Society News Section of the *Welding Journal* and posted on the AWS web site at: <http://www.aws.org/technical/d1/>.

Suggestions. Your comments for improving AWS D1.4/D1.4M:2011, *Structural Welding Code—Reinforcing Steel* are welcome. Submit comments to the Managing Director, Technical Services Division, American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126; telephone (305) 443-9353; fax (305) 443-5951; e-mail info@aws.org; or via the AWS web site <<http://www.aws.org>>.

Table of Contents

| | Page No. |
|--|-----------------|
| <i>Personnel</i> | v |
| <i>Foreword</i> | vii |
| <i>Table of Contents</i> | ix |
| <i>List of Tables</i> | xi |
| <i>List of Figures</i> | xi |
| 1. General Provisions | 1 |
| 1.1 Scope | 1 |
| 1.2 Application | 1 |
| 1.3 Reinforcing Steel Base Metal | 1 |
| 1.4 Welding Processes | 2 |
| 1.5 Definitions | 2 |
| 1.6 Welding Symbols | 2 |
| 1.7 Safety Precautions | 3 |
| 1.8 Standard Units of Measurement | 3 |
| 1.9 <u>Reference Documents</u> | 3 |
| 2. Allowable Stresses | 5 |
| 2.1 Base-Metal Stresses | 5 |
| 2.2 Allowable Stresses in Welds | 5 |
| 2.3 Effective Weld Areas, Lengths, Throats, and Sizes | 5 |
| 3. Structural Details | 9 |
| 3.1 Transition in Bar Size <u>Number</u> | 9 |
| 3.2 Eccentricity | 9 |
| 3.3 Joint Types | 9 |
| 3.4 Direct Butt Joints | 9 |
| 3.5 Indirect Butt Joints | 9 |
| 3.6 Lap Joints | 9 |
| 3.7 Interconnection of Precast Members | 9 |
| 4. Workmanship | 17 |
| 4.1 Preparation of Base Metal | 17 |
| 4.2 Assembly | 17 |
| 4.3 Control of Distortion, Shrinkage, and Heat | 17 |
| 4.4 Quality of Welds | 18 |
| 5. Technique | 21 |
| 5.1 Filler Metal Requirements | 21 |
| 5.2 Minimum Preheat and Interpass Temperature Requirements | 21 |
| 5.3 Welding Environment | 21 |
| 5.4 Arc Strikes | 22 |
| 5.5 Weld Cleaning | 22 |
| 5.6 Tack Welds | 22 |
| 5.7 Progression of Welding | 22 |
| 5.8 Welding of Coated Base Metal | 22 |
| 5.9 SMAW Electrodes | 22 |

| | | |
|-----------|--|----|
| 5.10 | <u>GMAW Electrodes</u> | 23 |
| 5.11 | <u>FCAW Electrodes</u> | 23 |
| 5.12 | <u>Shielding Gas</u> | 23 |
| 6. | Qualification | 27 |
| 6.1 | General | 27 |
| 6.2 | WPS Qualification | 27 |
| 6.3 | Welder Qualification | 29 |
| 6.4 | Retests | 31 |
| 6.5 | Period of Effectiveness | 31 |
| 6.6 | Records | 32 |
| 7. | Inspection | 45 |
| 7.1 | General Requirements | 45 |
| 7.2 | Inspection of Base Metals | 45 |
| 7.3 | Inspection of WPS Qualification and Equipment | 45 |
| 7.4 | Inspection of Welder Qualifications | 45 |
| 7.5 | Inspection of Work and Records | 45 |
| 7.6 | Obligations of the Contractor | 46 |
| 7.7 | Nondestructive Testing | 46 |
| 7.8 | Personnel Qualification | 46 |
| 7.9 | Radiographic Testing | 47 |
| | Annex A (Informative)—Sample Welding Forms | 53 |
| | Annex B (Informative)—Nominal Dimensions of ASTM Standard Reinforcing Bars | 59 |
| | Annex C (Informative)—Guidelines for the Preparation of Technical Inquiries for Structural Welding Committee | 61 |
| | Annex D (Informative)—Safe Practices | 63 |
| | Annex E (Informative)—Temperature-Moisture Content Charts | 71 |
| | List of AWS Documents on Structural Welding Code | 73 |

List of Tables

| Table | Page No. |
|-------|--|
| 2.1 | Allowable Stresses in Welds 6 |
| 3.1 | CJP Groove Weld Requirements for Direct Butt Joints 10 |
| 4.1 | Radiographic Acceptance Criteria 18 |
| 5.1 | Matching Filler Metal Requirements 24 |
| 5.2 | Minimum Preheat and Interpass Temperatures. 25 |
| 5.3 | Permissible Atmospheric Exposure of Low-Hydrogen Electrodes. 25 |
| 6.1 | <u>Prequalified WPS Fillet Weld Requirements</u> 32 |
| 6.2 | PQR Essential Variable Changes Requiring WPS Requalification for SMAW, GMAW, and FCAW. 33 |
| 6.3 | Number and Type of Tests for WPS Qualification 34 |
| 6.4 | Welder Qualification—Number, Type of Test, Production Welds, and Positions Qualified 35 |
| 6.5 | <u>Macroetch Acceptance Criteria</u> 36 |
| 7.1 | Hole-Type Image Quality Indicator (IQI) Requirements 50 |

List of Figures

| Figure | Page No. |
|--------|---|
| 2.1 | Effective Throat for Flare-Groove Welds 7 |
| 3.1 | Direct Butt Joints Showing Transition Between Bars of Different Sizes 10 |
| 3.2 | Direct Butt Joints. 11 |
| 3.3 | Indirect Butt Joints 12 |
| 3.4 | Lap Joints 13 |
| 3.5 | Details of Joints of Anchorages, Base Plates, and Inserts. 14 |
| 4.1 | <u>Minimum Distance to Cold Bending Radius Tangent Points</u> 19 |
| 4.2 | <u>Acceptable and Unacceptable Weld Profiles</u> 20 |
| 6.1 | Direct Butt Joint Test Positions for Groove Welds. 36 |
| 6.2 | Indirect Butt Joint Test Positions for Flare-Groove Welds or Fillet Welds 37 |
| 6.3 | Positions of Groove Welds 38 |
| 6.4 | Positions of Fillet Welds 39 |
| 6.5 | Full Section Tension Test Specimens for WPS Qualification Tests 40 |
| 6.6 | Full Section Tension Test and Macroetch Test Specimens for Welder Qualification Tests. 42 |
| 6.7 | <u>Bend Test Specimen for Welder Qualification Tests</u> 43 |
| 7.1 | <u>Source Position</u> 51 |
| 7.2 | <u>Film Placement</u> 52 |
| E.1 | Temperature-Moisture Content Chart to be Used in Conjunction with Testing Program to Determine Extended Atmospheric Exposure Time of Low-Hydrogen Electrodes. 66 |
| E.2 | Application of Temperature-Moisture Content Chart in Determining Atmospheric Exposure Time of Low-Hydrogen Electrodes 67 |

This page is intentionally blank.

Structural Welding Code—Reinforcing Steel

1. General Provisions

1.1 Scope

The code shall apply to the welding of the following:

1. Reinforcing steel to reinforcing steel, and
2. Reinforcing steel to carbon or low-alloy structural steel.

When the code is stipulated in contract documents, conformance with all provisions shall be required, except for those provisions that the Engineer or contract documents specifically modifies or exempts.

1.2 Application

1.2.1 This code shall be used in conjunction with the prescribed general building code requirements and is applicable to all welding of reinforcing steel, using the processes listed in 1.4, and performed as a part of reinforced concrete construction or in the manufacture of precast concrete components.

1.2.2 The weldments specified in this code shall not be used where impact properties are a requirement of the general specification. Impact testing requirements of welded reinforcing bars are not included in this code.

1.2.3 All references to the need for approval shall be interpreted to mean approval by the Engineer.

1.3 Reinforcing Steel Base Metal

1.3.1 Reinforcing steel base metal in this code shall conform to the requirements of the latest edition of one of the ASTM specifications listed within this paragraph. Combinations of any of these reinforcing steel base metals, when welded, shall use a WPS (welding procedure specification) qualified in conformance with Clause 6:

1. ASTM A 82/A 82M
2. ASTM A 496/A 496M
3. ASTM A615/A615M
4. ASTM A 706/A 706M
5. ASTM A 767/A 767M zinc-coated (galvanized) steel reinforcing bars that meet the requirements of ASTM A615/615M or ASTM A706/706M
6. ASTM A 775/A 775M epoxy-coated steel reinforcing bars that meet the requirements of ASTM A615/615M or ASTM A706/706M
7. ASTM A 934/A 934M epoxy-coated prefabricated steel reinforcing bars that meet the requirements of ASTM A615/615M or ASTM A706/706M

Manufacturing and testing requirements for mats and fabric are covered by the respective ASTM specification. For joining the ASTM A 82/A 82M and A 496/A 496M to other reinforcing wires, reinforcing bars, or structural steels, the Engineer shall specify filler metal and the provisions of this code shall apply.

1.3.2 When a reinforcing steel not listed in 1.3.1 is approved under the provisions of the general building code or by the Engineer, its chemical composition and carbon equivalent shall be provided and welding procedure shall be qualified in accordance with the requirements of 6.2 and all other requirements prescribed by the Engineer.

1.3.3 Base metal, other than those previously listed, shall be one of the structural steels listed in the latest edition of AWS D1.1, *Structural Welding Code—Steel*, or any steel stipulated in the contract documents or approved by the Engineer.