

AWS D17.3/D17.3M:2021-AMD1
An American National Standard



Specification for Friction Stir Welding of Aluminum Alloys for Aerospace Applications



second printing, August 2023



**AWS D17.3/D17.3M:2021-AMD1
An American National Standard**

**Approved by the
American National Standards Institute
October 2, 2020
Amendment: July 18, 2023**

Specification for Friction Stir Welding of Aluminum Alloys for Aerospace Applications

3rd Edition

Revises AWS D17.3/D17.3M:2016

Prepared by the
American Welding Society (AWS) D17 Committee on Welding in the Aircraft and Aerospace Industry

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This specification covers the general requirements for the friction stir welding of aluminum alloys for aerospace applications. It includes the requirements for weldment design, qualification of personnel and procedures, fabrication, and inspection.



ISBN Print: 978-1-64322-151-9
ISBN PDF: 978-1-64322-152-6
©2020 by American Welding Society
All rights reserved

Printed in the United States of America
Amendment: Second Printing, September 2023

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: www.copyright.com.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be revised, corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex E). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS D17 Committee on Welding in the Aircraft and Aerospace Industry. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS D17 Committee on Welding in the Aircraft and Aerospace Industry and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS D17 Committee on Welding in the Aircraft and Aerospace Industry to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Personnel (Amendment)

AWS D17 Committee on Welding in the Aircraft and Aerospace Industries

B. Worley, Chair	<i>GE Aerospace</i>
A. Pfaller, Vice Chair	<i>Miller Electric TIG Services</i>
P. Daum, 2 nd Vice Chair	<i>Rolls-Royce Corporation</i>
M. Diaz, Secretary	<i>American Welding Society</i>
R. Beil	<i>Northrop Grumman Corporation</i>
J. G. Bollin	<i>GE Aerospace</i>
G. Coleman	<i>CWICLLC</i>
C. Dickson, III	<i>Lockheed Martin Aeronautics</i>
R. Ding	<i>NASA-Marshall Space Flight Center</i>
H. Doucette	<i>Consultant</i>
R. Durda	<i>The Nordam Group</i>
S. Krem	<i>Howmet Aerospace</i>
M. R. Lanouette	<i>The Boeing Company</i>
M. Ludmer	<i>Advanced Weldtec Inc.</i>
R. Maust, III	<i>RTX – Raytheon Missiles and Defense</i>
L. Morris	<i>RTX – Raytheon Missiles and Defense</i>
S. H. Murray	<i>NASA Kennedy Space Center</i>
M. Nordin	<i>Rolls-Royce Corporation</i>
E. Przybylowics	<i>Blue Origin</i>
S. Rose	<i>The Boeing Company</i>
M. Sapp	<i>NAVAIR FRC-East</i>
D. Sheldon	<i>Roll Forming Corporation</i>
G. Trepus	<i>Blue Origin</i>
R. Trudelle	<i>Pro-Weld Services LLC</i>

Advisors to the AWS D17 Committee on Welding in the Aircraft and Aerospace Industries

R. Adams	<i>Consultant</i>
M. Bernasek	<i>C-SPEC</i>
C. Carl	<i>NASA Kennedy Space Center</i>
R. Freeman	<i>Performance Review Institute</i>
W. Guo	<i>Honeywell</i>
D. Ponder	<i>Triumph Airborne Structures</i>
J. Thyssen	<i>Consultant</i>

AWS D17J Subcommittee on Friction Welding

R. Ding, Chair	<i>NASA-Marshall Space Flight Center</i>
S. Rose, Vice Chair	<i>The Boeing Company</i>
M. Diaz, Secretary	<i>American Welding Society</i>
G. Coleman	<i>CWICLLC</i>
Z. Courtright	<i>NASA</i>
R. J. Durda	<i>The Nordam Group</i>
R. Freeman	<i>Performance Review Institute</i>
D. J. Huggett	<i>Blue Origin</i>

L. Johannes	<i>NASA</i>
E. Karlen	<i>UTC Aerospace Systems</i>
S. Krem	<i>Howmet Aerospace</i>
M. Petersen	<i>Blue Origin</i>
T. Stotler	<i>EWI</i>
R. Mulcahy	<i>Blue Origin</i>
B. Tweedy	<i>HFW Solutions</i>

Advisors to the AWS D17J Subcommittee on Friction Welding

R. W. Anderson	<i>Jacobs Engineering</i>
D. Hoyt	<i>Space Exploration Technologies Corp.</i>
R. Jones	<i>NASA</i>
R. Maust, III	<i>RTX – Raytheon Missiles and Defense</i>
G. Trepus	<i>Blue Origin</i>

Personnel (Original)

AWS D17 Committee on Welding in the Aircraft and Aerospace Industries

G. Coleman, Chair	<i>Consultant</i>
S. H. Murray, Vice Chair	<i>NASA Kennedy Space Center</i>
B. Worley, Second Vice Chair	<i>General Electric Aviation</i>
M. Diaz, Secretary	<i>American Welding Society</i>
J. T. Amin	<i>Lockheed Martin Aeronautics Company (retired)</i>
R. Beil	<i>Northrop Grumman Corporation</i>
M. Bernasek	<i>C-SPEC</i>
C. Carl	<i>NASA Kennedy Space Center</i>
J. Carruth	<i>Lockheed Martin Missiles & Fire Control</i>
P. Daum	<i>Rolls-Royce Corporation</i>
R. Ding	<i>NASA-Marshall Space Flight Center</i>
H. Doucette	<i>Consultant</i>
R. Durda	<i>The Nordam Group</i>
R. Maust, III	<i>Raytheon Integrated Defense Systems</i>
L. Morris	<i>Raytheon Integrated Defense Systems</i>
M. Nordin	<i>Rolls-Royce Corporation</i>
A. Pfaller	<i>Miller Electric TIG Services</i>
E. Przybylowics	<i>Blue Origin LLC</i>
G. Rolla	<i>Advanced Weldtec Inc.</i>
M. Sapp	<i>NAVAIR, MRO Engineering, FRC-East</i>
D. Sheldon	<i>Roll Forming Corporation</i>
J. Thyssen	<i>Consultant</i>
G. Trepus	<i>Boeing Research and Technology</i>
R. Trudelle	<i>Delta Air Lines</i>

Advisors to the AWS D17 Committee on Welding in the Aircraft and Aerospace Industries

R. Adams	<i>Consultant</i>
M. Bernath	<i>Consultant</i>
S. Dilcher	<i>Lockheed Martin Aeronautics Company</i>
R. Freeman	<i>TWI-The Welding Institute</i>
W. Guo	<i>Honeywell</i>
I. Harris	<i>Genesis Systems</i>
J. Pearson Jr	<i>LTK Engineering Services</i>
D. Ponder	<i>Triumph Airborne Solutions</i>
C. Sauer	<i>NAVAIR, MRO Engineering, FRC-East</i>
G. Stahle	<i>Navistar</i>

AWS D17J Subcommittee on Friction Welding

R. Ding, Chair	<i>NASA</i>
S. Rose, Vice Chair	<i>The Boeing Company</i>
M. Diaz, Secretary	<i>American Welding Society</i>
R. W. Anderson	<i>Vivace Corp.</i>
J. Carruth	<i>Lockheed Martin Missiles & Fire Control</i>

G. Coleman	<i>Consultant</i>
J. Comfort	<i>The Boeing Company</i>
R. J. Durda	<i>The Nordam Group</i>
R. Freeman	<i>TWI-The Welding Institute</i>
D. J. Huggett	<i>Vivace Corp.</i>
L. Johannes	<i>NASA</i>
R. Jones	<i>Jacobs Engineering</i>
E. Karlen	<i>UTC Aerospace Systems</i>
S. Krem	<i>EvoTech LLC</i>
M. Petersen	<i>Blue Origin</i>
T. Stotler	<i>EWI</i>

Advisors to the AWS D17J Subcommittee on Friction Welding

J. Bernath	<i>Consultant</i>
D. Hoyt	<i>Consultant</i>
R. Maust, III	<i>Raytheon Integrated Defense Systems</i>
G. Rolla	<i>California Welding Institute</i>
I. Stol	<i>ALCOA, Incorporated</i>
G. Trepus	<i>Boeing Research and Technology</i>

Foreword

This foreword is not part of this standard but is included for informational purposes only.

In the fall of 1993, aerospace welding personnel gathered together under the auspices of the American Welding Society (AWS) to develop an aerospace fusion welding specification to replace MIL-STD-1595A, *Qualification of Aircraft, Missile, and Aerospace Fusion Welders*, and MIL-STD-2219, *Fusion Welding for Aerospace Applications*. The result of this initial meeting was the formation of the AWS D17 Committee on Welding in the Aircraft and Aerospace Industries. The overriding theme voiced by the committee members was that the aviation industry had changed and a new specification was needed. In 2001, after years of hard work by the committee members, the American Welding Society issued AWS D17.1:2001, *Specification for Fusion Welding for Aerospace Applications*.

Specifications used for aerospace welding deal primarily with fusion welding, except for the relatively few that deal with friction welding. Fusion welding is used to produce the vast majority of large, structural, welded components, as opposed to friction welding, which usually is used to join smaller, circular cross-section detail parts. In 1991, The Welding Institute, in the United Kingdom, patented a new welding process called friction stir welding (FSW). The question soon arose as to which requirements were necessary to specify and control this new welding process. Fusion welding specifications could not adequately address FSW because it is a solid-state welding process. Friction welding specifications also could not adequately address the FSW process because, unlike friction welding, the FSW process uses a third body, the welding tool.

The AWS D17 Committee on Welding in the Aircraft and Aerospace Industries determined that it was necessary to form a subcommittee to write a specification for friction stir welding. It was appropriate that the setting for the subcommittee's kickoff meeting was at the Kennedy Space Center in Florida. Kennedy Space Center is where the first friction stir welded commercial aerospace component, the fuel tank for the Delta launch vehicle, went into service. Representatives from industry, welding institutes, government agencies, and universities met to dedicate themselves to form a specification for the friction stir welding of aluminum for aerospace applications. AWS D17.1:2001, served as the model for this specification.

This is the third edition of AWS D17.3/D17.3M, *Specification for Friction Stir Welding of Aluminum Alloys for Aerospace Applications*. A vertical line in the margin or underlined text in clauses, tables, or figures indicates an editorial or technical change from the 2016 edition.

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, AWS D17 Committee on Welding in the Aircraft and Aerospace Industries, American Welding Society, 8669 NW 36 St, #130, Miami, FL 33166.

This page is intentionally blank.

Amendment

The following Amendments have been identified and are incorporated in this reprint.

Amendment Number: 1

Subject: The welding operators are qualified to the Class of weld specified on the WPS and should be noted on the qualification record. Therefore, the last sentence in Subclause 7.1.2 has been amended as follows to revert to the previous version of the specification:

7.1.2 Test Weld. One of the test coupons in Figures 7.1 through 7.4 shall be used for the welding operator qualification test. The test coupon shall be welded in accordance with a WPS. The operator being qualified shall verify all aspects of the weld that would normally be required to make the weld in the production operation, in accordance with the WPS. Operators shall be qualified to the class of weld specified on the WPS, unless otherwise approved by the Engineering Authority.

This page is intentionally blank.

Table of Contents

	Page No.
<i>Personnel (Amendment)</i>	v
<i>Personnel (Original)</i>	vii
<i>Foreword</i>	ix
<i>List of Tables</i>	xv
<i>List of Figures</i>	xv
1. General Requirements	1
1.1 Scope	1
1.2 Units of Measure	1
1.3 Safety	1
2. Normative References	1
3. Terms and Definitions	2
4. General Requirements for FSW	9
4.1 Classification	9
4.2 Approval	9
4.3 Drawing Precedence	9
4.4 Specification Precedence	9
5. Design of Weld Joints	9
5.1 Weldment Design Data	9
5.2 Drawing Information Requirements	9
6. Development and Qualification of a Welding Procedure	10
6.1 General	10
6.2 Selection of a Welding Procedure Specification Qualification Method	10
6.3 Welding	11
6.4 Evaluation of Test Welds	12
6.5 Preparation of a Welding Procedure Specification (WPS)	14
6.6 Welding Procedure Qualification Record (WPQR)	17
6.7 Qualification Limits	17
6.8 Welding Procedure Specification	18
6.9 Revising a WPQR or WPS	18
7. Welding Operator Qualification	18
7.1 Qualification Requirements	18
7.2 Qualification Limitations	19
7.3 Qualification/Certification Validity	19
7.4 Test Records	19
8. Fabrication	22
8.1 Welding	22
8.2 Welding Equipment Requirements	22
8.3 Friction Stir Welding Tool	22
8.4 Preweld Joint Preparation and Fit-Up	22
8.5 Tack Welds	23
8.6 Postweld Finishing	23

8.7	Weld Identification Requirements	23
8.8	Acceptance Inspection	23
<u>8.9</u>	<u>Rework</u>	23
<u>8.10</u>	<u>Repair</u>	23
9.	Inspection	24
9.1	Inspection Personnel	24
9.2	Visual Weld Inspection	24
9.3	Nondestructive Examination	24
9.4	Acceptance Criteria	24
Annex A	(Normative)—Illustrations of Test Specimens and Test Fixtures	27
Annex B	(Informative)—Example of Welding Procedure Specification Forms	31
Annex C	(Informative)—Examples of Welding Procedure Qualification Record Forms	33
Annex D	(Informative)—Example of a Welding Operator Qualification Test Record Form	39
Annex E	(Informative)—Requesting an Official Interpretation on an AWS Standard	41
	List of AWS Documents on Welding in the Aircraft and Aerospace Industries	43

List of Tables

Table		Page No.
6.1	Sequence for Qualifying a Welding Procedure Specification	10
6.2	Methods for Qualifying a Welding Procedure Specification	10
6.3	Destructive Tests Required for Qualifying a Welding Procedure	14
6.4	Efficiency Requirements for Welded Butt Joint Tensile Strength	14
<u>6.5</u>	<u>Essential Variable Ranges</u>	18
9.1	Acceptance Criteria	25

List of Figures

Figure		Page No.
3.1	Friction Stir Welding Nomenclature	4
3.2	Angular Distortion/ <u>Angular Mismatch</u>	5
3.3	Cavity	5
3.4	Flash	5
<u>3.5</u>	<u>Hook</u>	6
<u>3.6</u>	<u>Varying Degrees of Incomplete Joint Penetration</u>	6
<u>3.7</u>	<u>Linear Mismatch</u>	6
<u>3.8</u>	<u>Self-Reacting Tool</u>	7
<u>3.9</u>	<u>Tool Offset</u>	7
<u>3.10</u>	<u>Components of Tool</u>	8
<u>3.11</u>	<u>Stationary Shoulder Friction Stir Welding (SSFSW)</u>	8
6.1	Flow Diagram for the Development and Qualification of a Welding Procedure Specification	11
6.2	Location of Square-Groove Weld Test Specimens—Pipe	12
6.3	Location of Square-Groove Weld Test Specimens—Plate	13
6.4	Location of Fillet Weld Test Specimens—Plate	15
6.5	Location of Seam Weld Test Specimens—Plate	16
7.1	Seam Weld Test in Plate	20
7.2	Square-Groove Weld Test in Pipe	20
7.3	Square-Groove Weld Test in Plate	21
7.4	Seam Weld Test in Pipe	21
A.1	Reduced Section Tension Specimen—Rectangular	27
A.2	Reduced Section Tension Specimen—Round	28
A.3	Alternate Tension Specimen for Pipe 3 in [76 mm] O.D. or Less	28
A.4	Alternate Tension Specimen for Pipe 2 in [51 mm] O.D. or Less	29
B.1	Example of a Welding Procedure Specification Form	31
C.1	Example Number One of a Welding Procedure Qualification Record Form	33
C.2	Example Number Two of a Welding Procedure Qualification Record Form	35
D.1	Example of a Welding Operator Qualification Test Record Form	39

This page is intentionally blank.

Specification for Friction Stir Welding of Aluminum Alloys for Aerospace Applications

1. General Requirements

1.1 Scope. This specification contains the requirements for friction stir welding (FSW) of aluminum aerospace hardware. The requirements include design of welded joints, qualification of procedures and operators, fabrication and inspection. The FSW methods covered by this specification are conventional FSW, retractable probe FSW, stationary shoulder FSW, and self-reacting FSW.

1.2 Units of Measure. This standard makes use of both U.S. Customary Units and the International System of Units (SI). The latter are shown within brackets ([]) or in appropriate columns in tables and figures. The measurements may not be the exact equivalents; therefore, each system must be used independently.

1.3 Safety. Safety and health issues and concerns are beyond the scope of this standard and therefore are not addressed herein. Safety and health information is available from the following sources:

American Welding Society:

- (1) ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*
- (2) AWS Safety and Health Fact Sheets
- (3) Other safety and health information on the AWS website.

Material or Equipment Manufacturers:

- (1) Safety Data Sheets supplied by materials manufacturers
- (2) Operating Manuals supplied by equipment manufacturers.

Applicable Regulatory Agencies

Work performed in accordance with this standard may involve the use of materials that have been deemed hazardous, and may involve operations or equipment that may cause injury or death. This standard does not purport to address all safety and health risks that may be encountered. The user of this standard should establish an appropriate safety program to address such risks as well as to meet applicable regulatory requirements. ANSI Z49.1 should be considered when developing the safety program.

2. Normative References

The documents listed below are referenced within this publication and are mandatory to the extent specified herein. For undated references, the latest edition of the referenced standard shall apply. For dated references, subsequent amendments or revisions of the publications may not apply since the relevant requirements may have changed.

AWS documents:

- AWS A1.1, *Metric Practice Guide for the Welding Industry*;
- AWS A2.4, *Standard Symbols for Welding, Brazing and Nondestructive Examination*;