


AWS D8.9M:2012
An American National Standard



Test Methods for Evaluating the Resistance Spot Welding Behavior of Automotive Sheet Steel Materials



American Welding Society®



AWS D8.9M:2012
An American National Standard

Approved by the
American National Standards Institute
February 22, 2012

Test Methods for Evaluating the Resistance Spot Welding Behavior of Automotive Sheet Steel Materials

3rd Edition

Supersedes AWS/SAE D8.9M:2002

Prepared by the
American Welding Society (AWS) D8 Committee on Automotive Welding

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This document presents standard test methods for evaluating the resistance spot welding behavior of automotive sheet steels. The document contains a number of tests and test methods useful in determining the resistance spot welding performance of coated and uncoated automotive sheet steels of all strength levels and compositions. The test methods are designed to assess current range, electrode endurance, and weld properties of automotive sheet steels. The weld property tests include tests for hold time sensitivity, weld hardness, shear tension strength, and cross tension strength.



American Welding Society®

550 N.W. LeJeune Road, Miami, FL 33126

International Standard Book Number: 978-0-87171-808-2
American Welding Society
550 N.W. LeJeune Road, Miami, FL 33126
© 2012 by American Welding Society
All rights reserved
Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <www.copyright.com>.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While the AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be superseded by the issuance of new editions. This standard may also be corrected through publication of amendments or errata. It may also be supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda are posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

The AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

On occasion, text, tables, or figures are printed incorrectly, constituting errata. Such errata, when discovered, are posted on the AWS web page (www.aws.org).

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Technical Services Division, 550 N.W. LeJeune Road, Miami, FL 33126 (see Annex G). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS D8 Committee on Automotive Welding. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are required and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS D8 Committee on Automotive Welding and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS D8 Committee on Automotive Welding to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

Personnel

AWS D8 Committee on Automotive Welding

D. L. Galiher, Chair	<i>Tower International</i>
T. Coon, 1st Vice Chair	<i>Ford Motor Company</i>
M. D. Tumuluru, 2nd Vice Chair	<i>U.S. Steel</i>
E. H. Abrams, Secretary	<i>American Welding Society</i>
G. Armstrong	<i>Yachiyo of Ontario Manufacturing, Incorporated</i>
J. E. Beckham	<i>Chrysler Group LLC</i>
J. C. Bohr	<i>General Motors</i>
W. H. Brafford	<i>Tuffaloy Products, Incorporated</i>
J. W. Dolfi	<i>Consultant</i>
F. W. Hunt	<i>Hitachi America, Limited</i>
J. G. Hunt	<i>AET Integration, Incorporated</i>
C. Jiang	<i>AET Integration, Incorporated</i>
S. C. Kelley	<i>ArcelorMittal</i>
D. P. Kelly	<i>Fusion Welding Solutions</i>
D. R. Kolodziej	<i>Ford Motor Company (Retired)</i>
D. F. Maatz, Jr.	<i>RoMan Engineering Services, Incorporated</i>
T. W. Morrissett	<i>RoMan Engineering Services, Incorporated</i>
J. S. Noruk	<i>Servo Robot Corporation</i>
W. F. Qualls	<i>Consultant</i>

Advisor to the AWS D8 Committee on Automotive Welding

J. F. Hinrichs	<i>Friction Stir Link, Incorporated</i>
----------------	---

AWS D8D Subcommittee on Automotive Resistance Spot Welding

J.C. Bohr, Chair	<i>General Motors</i>
W. F. Qualls, 1st Vice Chair	<i>Consultant</i>
H. Zhang, 2nd Vice Chair	<i>University of Toledo</i>
E. H. Abrams, Secretary	<i>American Welding Society</i>
J. E. Beckham	<i>Chrysler Group LLC</i>
E. Biro	<i>ArcelorMittal</i>
W. H. Brafford	<i>Tuffaloy Products, Incorporated</i>
T. Coon	<i>Ford Motor Company</i>
J. W. Dolfi	<i>Consultant</i>
J. G. Hunt	<i>AET Integration, Incorporated</i>
C. Jiang	<i>AET Integration, Incorporated</i>
D. P. Kelly	<i>Fusion Welding Solutions</i>
M. Kimchi	<i>Edison Welding Institute</i>
M. Kuo	<i>ArcelorMittal</i>
D. F. Maatz, Jr.	<i>RoMan Engineering Services, Incorporated</i>
T. W. Morrissett	<i>RoMan Engineering Services, Incorporated</i>
T. V. Natale	<i>AK Steel Corporation</i>
C. J. Orsette	<i>Fusion Welding Solutions</i>
E. Pakalnins	<i>RoMan Engineering Services, Incorporated</i>
W. Peterson	<i>Edison Welding Institute</i>

AWS D8D Subcommittee on Automotive Resistance Spot Welding (Continued)

N. S. Scotchmer	<i>Huys Industries Limited</i>
T. Sparschu	<i>TMS Solutions</i>
D. J. Spinella	<i>ALCOA Technical Center</i>
M. D. Tumuluru	<i>U.S. Steel</i>

Advisors to the AWS D8D Subcommittee on Automotive Resistance Spot Welding

W. H. Trojanowski	<i>Chrysler Group LLC</i>
M. Hebert	<i>General Motors (Retired)</i>

Foreword

This foreword is not part of AWS D8.9M:2012, *Test Methods for Evaluating the Resistance Spot Welding Behavior of Automotive Sheet Steel Materials*, but is included for informational purposes only.

Since its publication in 1997, the AWS D8.9 standard has been widely used by steel companies and automotive companies alike to test the weldability of sheet steels for various automotive applications. This document evolved from the Auto/Steel Partnership of the American Iron and Steel Institute's publication, *Weld Quality Test Methods Manual*. The AWS D8D Subcommittee, which includes members of the Auto/Steel Partnership's Standardized Welding Test Method Task Force, acknowledges the important contributions made by the Auto/Steel Partnership's staff and members in the development and revision of this document.

With the introduction of new advanced high strength steels into automotive production there is a strong need to test these new steels. Therefore, a set of weld schedules has been added in this revision to address this need. Further, a new Design of Experiments (DoE) test method has been included to examine the robustness of advanced high strength steels to variations in welding parameters that typically occur under shop-floor conditions. The procedure outlined in the DoE testing method has been validated at four independent testing laboratories.

This document not only contains test methods for evaluating the welding behavior of sheet steels, but also covers areas essential to using these test methods in obtaining an accurate assessment of the material and its welding attributes.

Listed below are the key test methods described in this document:

- Sampling and characterization of test material
- Equipment setup and electrode installation
- Electrode conditioning and weld size stabilization
- Endurance (electrode life) testing
- Current level/current range testing
- Weld property testing
- Current break-through testing
- Design of Experiments testing

The sampling and material characterization procedures, equipment setup and electrode installation procedures, and electrode conditioning/weld size stabilization procedures are common to all test methods. In the endurance test, the "endurance limit" (defined as the number of acceptable welds made during the test) is the key welding performance measure that is determined by this test. Other welding behavior measures determined in this test are current levels and current range. Weld button characteristics are assessed by destructive peel testing of weld samples.

The weld property tests are designed to determine hold-time sensitivity, weld button fracture mode, shear tension strength, cross tension strength, metallurgical properties, and hardness of welds made with the test material. The weld property testing is now required at two different weld sizes. Proper judgment should be exercised when interpreting the results of the weld property tests on higher strength steels (such as those with ultimate tensile strength greater than 500 MPa), especially with tests run at the minimum weld size. Welds in such higher strength steels may show interfacial fractures even at short hold times, especially at thicker gauges. The requirement to conduct the tests at the minimum weld size is included to generate more complete information on the behavior of such steels. A fracture classification chart has been added as an Annex D.

Current levels and current range are also determined during the weld property tests. The current break-through test is designed to evaluate the effects that sheet lubricants, conductive paints, or other surface treatments have on the initiation of spot welding current and nugget formation. The types of tests to use shall be specified by the party for whom the testing is to be performed. For some steels, all tests may be specified, while for others, only one test may be specified.

It should be noted that not all of the above tests are required to establish the resistance spot welding behavior of a given grade of steel. The current level/current range testing and weld property testing together generally provide a good indication of the resistance spot welding behavior, whereas the DoE testing is intended to examine the robustness of a given grade of high strength steel to variations in key process variables. The specific tests required to establish the resistance spot welding behavior of a given grade of steel should be agreed upon by the steel supplier (or test laboratory) and the automotive company (or buyer of the steel).

Users of this document have requested that subsequent updates to the document include provisions for the incorporation of other types of welding equipment, electrode caps, and weld schedules than those provided in the document. The inclusion of these alternative methods may permit the testing to be more customer-focused and allow for the determination of specific material and welding performance issues as they relate to a particular manufacturing situation. A commentary and discussion are provided in Annex E and are intended to serve as guidelines should the users of this document desire to utilize alternative test methods for the weld characterization of sheet steels.

It should be noted that, as the weldability evaluation procedures in alternative methods deviate from the procedure described in this document, they may add to the complexity and cost of the material evaluation. The type of evaluations required, and any deviations required to perform them, should be agreed upon between the party for whom the testing is to be performed and the testing laboratory.

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, AWS D8 Committee on Automotive Welding, American Welding Society, 550 N.W. LeJeune Road, Miami, FL 33126.

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>Foreword</i>	vii
<i>List of Tables</i>	xii
<i>List of Figures</i>	xiii
<i>List of Forms</i>	xv
1. Scope and Applicability	1
1.1 Scope	1
1.2 Standard Units of Measurement	2
1.3 Safety Precautions	2
2. Normative References	3
3. Terms and Definitions	3
4. Sample Preparation	6
4.1 Coupon Sizes	6
4.2 Total Sheet Quantity Requirements	6
4.3 Rolling Direction (RD) Orientation	8
4.4 Shearing Details	8
4.5 Surface Preparation	9
5. Material Characterization	9
5.1 Sheet Identification	11
5.2 Sheet Thickness	11
5.3 Coating Weight	11
5.4 Coating Composition	11
5.5 Substrate Composition	12
5.6 Mechanical Properties (if required)	12
5.7 Surface Roughness (if required)	12
6. Welding Parameters	12
6.1 Electrode Specifications and Dimensions	12
6.2 Welding Variables	12
6.3 Electrode Cooling	14
6.4 Weld Spacing and Overlap	14
6.5 Sample Orientation and Sequencing	16
6.6 Surface Orientation (Coated Sheet Steels Only)	17
6.7 Weld Size	17
7. Preferred Test Equipment	20
7.1 Welding Machine	20
7.2 Current/Weld Time Meter	21
7.3 Force Gauge	21
7.4 Electrode Cooling	21
7.5 Weld Counter	21
7.6 Calipers	21
7.7 Tip Dressing File	21
7.8 Tip Dressing Emery Paper	21

7.9	Carbon Paper	21
7.10	Tip Imprint Paper	21
7.11	Electrode Cooling Tubes	21
8.	Electrode Installation and Dressing Procedure	21
8.1	Electrode Measurements Before Installation and Electrode Installation	21
8.2	Custom Machined Electrodes.....	23
8.3	Electrode Dressing Option 1—Using Direct Electrode-Face Measurements	23
8.4	Electrode Dressing Option 2—Using Tip Imprints for Electrode-Face Measurements.....	24
8.5	Verification of Electrode Concentricity and Parallelism	26
9.	Electrode-Face and Weld-Size Stabilization Procedure	27
9.1	Introduction and Overview.....	27
9.2	Preparation	27
9.3	Stabilization Procedure	28
10.	Endurance Test.....	30
10.1	Introduction and Overview.....	30
10.2	Test Preparation.....	31
10.3	Initial I_{MIN} Current Determination	31
10.4	Initial I_{MAX} Current Determination.....	32
10.5	Endurance Test	32
10.6	Final I_{MIN} Current Determination	33
10.7	Final I_{MAX} Current Determination	33
10.8	Replication	34
10.9	Calculations for Mean Current Levels and Current Ranges.....	34
10.10	Endurance Test Report	34
11.	Weld Property Tests	35
11.1	Introduction and Overview.....	35
11.2	Test Preparation.....	35
11.3	I_{MIN} Current Determination	36
11.4	I_{MAX} Current Determination.....	36
11.5	Hold-Time Sensitivity (HTS) Test	37
11.6	Shear and Cross Tension Tests	41
11.7	Replication	45
11.8	Test Report	45
12.	Current Break-Through Test	46
12.1	Scope	46
12.2	Equipment	47
12.3	Test Materials	47
12.4	Test Preparation.....	47
12.5	Determination of the Current Break-Through Test Current (I_{CBT})	47
12.6	Welding the Current Break-Through Control and Test Samples	48
12.7	Analyzing the Welding Current Data	50
12.8	Test Report	50
13.	Design of Experiments (DoE) Test Procedure for Resistance Spot Welding Characterization of High Strength and Advanced High Strength Steels.....	51
13.1	Introduction and Overview.....	51
13.2	Equipment	51
13.3	Sample Preparation	52
13.4	B-Nose (Dome) Electrode Installation and Stabilization.....	52
13.5	DoE Procedure	52
13.6	Metallographic Evaluation	57

	Page No.
13.7 Weld Property Evaluation.....	57
13.8 DoE Analysis.....	59
13.9 Reporting.....	59
Annex A (Informative)—Electrodes	61
Annex B (Informative)—Data Forms.....	63
Annex C (Informative)—Optional Endurance Test Panel.....	89
Annex D (Informative)—Fracture Classification Charts.....	91
Annex E (Informative)—Procedural Guidelines for Alternative Testing Methods.....	101
Annex F (Informative)—Informative References	103
Annex G (Informative)—Guidelines for the Preparation of Technical Inquiries.....	105
List of AWS Documents on Automotive Welding	107

List of Tables

Table	Page No.
1	Classification of Steels for Resistance Spot Welding and Testing Purposes2
2	Coupon Dimensions and Estimated Material Requirements (Endurance Test).....7
3	Coupon Dimensions and Estimated Material Requirements (Weld Property Tests)7
4a	Welding Parameters for Groups 1 and 2 Steels..... 12
4b	Welding Parameters for Group 3 Steels 13
4c	Welding Parameters for Group 4 Steels 13
5	Weld Location, Spacing, and Overlap Dimensions for Peel-Test Samples 14
6	Weld Spacing and Edge Distances for Endurance Test and Electrode Conditioning Panel Samples..... 15
7	Default Initial Welding Currents29
8	Conditions/Combinations for Hold-Time Sensitivity (HTS) Tests.....37
9	Conditions/Combinations for Shear and Cross Tension Tests42
10	Shear Tension Sample Dimensions.....42
11	Cross Tension Sample Dimensions.....42
12	DoE Experimental Design51
13	DoE Factor Level Summary51
14	Electrode Dimensions55
15	DoE Default Initial Welding Currents (B-nose)55
16	DoE Weld Parameters, Bare-to-Bare Faying Surface Condition55
17	DoE Weld Parameters, Coated-to-Coated Faying Surface Condition55
18	DoE Run Matrix.....56
A.1	Electrode Specifications and Dimensions.....61
C.1	Coupon Dimensions, Weld Spacing, and Edge Distances for Optional Panels..... 89

List of Figures

Figure		Page No.
1	Surface and Rolling Direction Marking of Sheet	8
2	Trimmed Coil Width with Transferred RD Mark on Sheet	9
3A	Test Coupon Strips with Transferred Marks	10
3B	Endurance Test Panel Coupon Strips with Transferred Marks	10
4	Material Characterization Panel with Transferred Marks	11
5	Weld Location, Spacing, and Coupon Overlap for Peel-Test Samples	14
6	Weld Spacing and Edge Distances for Endurance Test and Electrode Conditioning Panel Samples	15
7	Top View of Peel Sample Orientations with Respect to Welding Machine Throat	16
8	Panel Sample Orientations (A and B) with Respect to the Welding Machine Throat	16
9	Surface Orientation of Peel-Test Samples	17
10	Surface Orientation of Weld Property Test Samples (Shear Tension Shown)	18
11	Example of Tab Removal to Allow for Proper Measurement of Weld Buttons	18
12A	Technique for Measuring Oval Weld Buttons	19
12B	Technique for Measuring Irregular Weld Buttons	19
13	Technique for Measuring the Weld Button and Fused Diameters of Partial Interfacial Fractures	20
14	Preferred Position of Cooling Tubes in Electrodes	22
15A	Individual Tip Imprint Schematic	26
15B	Composite Tip Imprint Schematic	27
16	Graphical Example of a Typical Stabilization Procedure	28
17	Graphical Example of the Endurance Test Procedure	31
18	Weld Layout for HTS Panels	38
19	Sectioning of Test Welds for Metallographic Examination and Hardness Testing	41
20	Cross-Sectioned Weld and Hardness Traverse	41
21	Schematic for Shear Tension Samples	43
22	Schematic for Cross Tension Samples	43
23	Schematic for Testing of Shear Tension Samples	45
24	Test Fixture Schematic for Testing of Cross Tension Samples	45
25	Surface Orientation of CBT Peel-Test Samples	48
26A	Example of Current Analyzer Printout for Weld with 0 Half-Cycles of CBTT	49
26B	Example of Current Analyzer Printout for Weld with 1 Half-Cycle of CBTT	49
26C	Example of Current Analyzer Printouts for Welds with 8 Half-Cycles of CBTT	49
27A	Electrode Geometry—Female B-nose electrode cap, 15.87 mm body diameter	53
27B	Electrode Geometry—Female B-nose electrode cap, 19.0 mm body diameter	54
28	Examples of Edge Welds	58
29	Surface Cracks	59
30	Indentation Measurement	60
A.1	Spot Welding Electrode Diagram	62
C.1	Panel Row Sequencing, Weld Spacing, and Edge Distances for Rows 1 through 3 on the Optional Panel	90
C.2	Panel Row Sequencing, Weld Spacing, and Edge Distances for Rows 4 through 6 on the Optional Panel	90
D.1	Fracture Mode 1—Button Pull	92
D.2	Fracture Mode 2—Partial Thickness Fracture with Button Pull	93
D.3	Fracture Mode 3—Partial Thickness Fracture	94
D.4	Fracture Mode 4—Interfacial Fracture with Button Pull and Partial Thickness Fracture	95

Figure		Page No.
D.5	Fracture Mode 5—Interfacial Fracture with Button Pull.....	96
D.6	Fracture Mode 6—Interfacial Fracture with Partial Thickness Fracture	97
D.7	Fracture Mode 7—Interfacial Fracture	98
D.8	Fracture Mode 8—No Fusion	99

List of Forms

Form	Page No.
B-1 Welding Data Sheet (Page 1).....	65
B-1 Welding Data Sheet (Page 2).....	66
B-2-DOPT1 Tip Imprint Data Sheet (Page 1).....	67
B-2-DOPT2 Tip Imprint Data Sheet (Page 1).....	68
B-2-DOPT1 or DOPT2 Tip Imprint Data Sheet (Page 2).....	69
B-3 Test Material Data Sheet (Page 1).....	70
B-3 Optional Material Data (Page 2)	71
B-4 Endurance Test Report (Page 1).....	72
B-4 Endurance Test Data (Page 2)	73
B-5 Weld Property Test Report (Page 1).....	74
B-5 Weld Property Test Data (Page 2)	75
B-5 Weld Property Test Data (Page 3)	76
B-5 Weld Property Test Data (Page 4)	77
B-6 Current Break-Through Test Report (Page 1)	78
B-6 Current Break-Through Test Data (Page 2)	79
B-7 DoE Welding Test Cover Sheet Report	80
B-8 DoE Welding Setup and Verification Report (Page 1)	81
B-8 DoE Welding Setup and Verification Report (Page 2)	82
B-9-ST DoE Welding Data Sheet with Measured Responses Report—Shear Tension	83
B-9-CT DoE Welding Data Sheet with Measured Responses Report—Cross Tension	86

Test Methods for Evaluating the Resistance Spot Welding Behavior of Automotive Sheet Steel Materials

1. Scope and Applicability

1.1 Scope. This document contains several standardized test methods that are designed to evaluate the resistance spot welding behavior of coated and uncoated sheet steels in a laboratory environment. The test methods allow for uniform testing of automotive sheet steels to determine the following:

- (1) The effect of the interaction between a sheet steel's coating (metallic, nonmetallic, or both) and the welding electrodes on electrode deterioration and weld size/quality behavior over an extended number of welds
- (2) Current levels and current range
- (3) Mechanical properties of welds at different weld sizes and hold times
- (4) Metallurgical and hardness properties of welds
- (5) The effects of sheet lubricants, conductive paints, or other surface treatment on current break-through
- (6) The robustness of a grade of steel to variations in key welding process variables

The test methods are intended for application in a laboratory environment to characterize certain aspects of the welding behavior of sheet steel products under controlled experimental conditions. **They are not intended to simulate production welding practices or to predict welding performance of a given grade of steel in production operations.** The test methods and parameters are designed to be used for sheet steels ranging in thickness from 0.6 mm to 3.0 mm. The tests may be used for sheet steel materials of all yield strengths typically used in automotive applications. In the endurance test, a minimum of two tests per material is recommended to obtain an accurate assessment. The endurance test was developed for low strength (tensile strength less than or equal to 300 MPa) coated steels of lighter gauges. This test is normally used for coated steels with tensile strength less than or equal to 500 MPa and gauges less than 1.2 mm. The weld property tests are designed primarily for gauges of 1.2 mm and heavier.

The specific type and number of tests that are required shall be at the discretion of the specifying party. While the test methods were developed to compare the welding behavior of different steel grades, they can be judiciously applied to evaluate other aspects of welding behavior. Not all of the above mentioned tests are required to establish the resistance spot welding behavior of a given grade of steel. The current level/current range testing and weld property testing together generally provide a good indication of the resistance spot welding behavior, whereas the DoE testing is intended to examine the robustness of a given grade of high strength steel to variations in key process variables.

The specific tests required to establish the resistance spot welding behavior of a given grade of steel should be agreed upon by the steel supplier (or test laboratory) and the automotive company (or buyer of the steel).

A commentary is provided in Annex D on alternative test methods and is intended to serve as a guide should the users of this document desire to utilize alternative test methods for the weld characterization of sheet steels. Because the weldability evaluation procedures in alternative methods deviate from the procedure described in this document, the use of the alternative test methods may add to the complexity and cost of the material evaluation. The type of evaluations required, and any deviations required to perform them, should be agreed upon between the party for whom the testing is to be performed and the testing laboratory.

Resistance spot welding behavior is dependent upon a wide variety of interacting material and weld process factors. To obtain repeatable and reproducible performance data, it is imperative that all experimental variables and the way a test is conducted be closely controlled. Therefore, the instructions for the various sampling and testing procedures in this manual are stated in mandatory language and should be followed as closely as possible. Deviations from the prescribed